



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
031
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON UHP 10W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DE0000484	DE0000516	PCA0032523
Sample Date		Client Info		29 May 2024	06 Oct 2023	03 Apr 2023
Machine Age	mls	Client Info		294823	279176	258300
Oil Age	mls	Client Info		294823	13086	10000
Filter Age	mls	Client Info		294823	13086	10000
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	15	8	7
Chromium	ppm	ASTM D5185m	>20	<1	<1	0
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	4	2	2
Lead	ppm	ASTM D5185m	>40	<1	0	0
Copper	ppm	ASTM D5185m	>330	2	1	<1
Tin	ppm	ASTM D5185m	>15	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	6	3	4
Potassium	ppm	ASTM D5185m	>20	3	3	<1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.3	0.1
Nitration	Abs/cm	*ASTM D7624	>20	8.8	7.4	5.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.4	18.0	15.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	0	0
Boron	ppm	ASTM D5185m	2	4	1	9
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	61	57	58
Manganese	ppm	ASTM D5185m	0	0	0	<1
Magnesium	ppm	ASTM D5185m	1010	998	883	969
Calcium	ppm	ASTM D5185m	1070	1116	972	1045
Phosphorus	ppm	ASTM D5185m	1150	1174	999	1008
Zinc	ppm	ASTM D5185m	1270	1301	1128	1257
Sulfur	ppm	ASTM D5185m	2060	3233	2889	3404
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.2	14.4	12.8
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.9	9.1	8.7
Visc @ 100°C	cSt	ASTM D445	15.52	13.6	13.9	14.2


FT-IR (Direct Trend)




Ferrous Alloys




Base Number




Non-ferrous Metals




Viscosity @ 100°C




Viscosity @ 40°C



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DE0000484 **Received** : 28 Jun 2024
Lab Number : 06224192 **Tested** : 01 Jul 2024
Unique Number : 11102389 **Diagnosed** : 01 Jul 2024 - Angela Borella
Test Package : FLEET (Additional Tests: KV40)

Iroquois Bar Corp.
 155 Commerce Drive
 Lacakwanna, NY
 US 14218
 Contact: Denver Persinger
 dpersinger@iroquoisbar.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: