
WEAR CONTAMINATION **FLUID CONDITION**

NORMAL SEVERE ABNORMAL

Machine Id

725056-310015

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
We advise that you check the fuel injection system. We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition.	Sample Number		Client Info		GFL0118201	GFL0118244	GFL0118184
	Sample Date		Client Info		20 Jun 2024	22 May 2024	25 Apr 2024
	Machine Age	hrs	Client Info		23801	23635	23465
	Oil Age	hrs	Client Info		700	170	600
	Filter Age	hrs	Client Info		700	0	0
	Oil Changed		Client Info		Not Changd	N/A	Changed
	Filter Changed		Client Info		Not Changd		Changed
	Sample Status				SEVERE	SEVERE	SEVERE
WEAR	Iron	ppm	ASTM D5185m	>80	26	14	13
	Chromium	ppm	ASTM D5185m	>5	1	<1	<1
All component wear rates are normal.	Nickel	ppm	ASTM D5185m	>2	0	0	0
	Titanium	ppm	ASTM D5185m		<1	0	0
	Silver	ppm	ASTM D5185m	>3	0	0	0
	Aluminum	ppm	ASTM D5185m	>30	2	1	3
	Lead	ppm	ASTM D5185m	>30	0	0	0
	Copper	ppm	ASTM D5185m	>150	<1	<1	<1
	Tin	ppm	ASTM D5185m	>5	0	0	0
	Vanadium	ppm	ASTM D5185m		0	<1	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	9	8	<u>^</u> 24
CONTAMINATION	Potassium	ppm	ASTM D5185m		0	<1	3
There is a high amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.	Fuel	%	ASTM D3524		▲ 10.8	▲ 11.8	▲ 8.4
	Water	,,,	WC Method		NEG	NEG	NEG
	Glycol		WC Method		NEG	NEG	NEG
	Soot %	%	*ASTM D7844	>3	1.1	0.7	0.6
	Nitration	Abs/cm	*ASTM D7624	>20	12.7	10.3	10.3
	Sulfation	Abs/.1mm	*ASTM D7415	>30	22.3	19.8	19.5
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		5	5	2
I LOID CONDITION	Boron	ppm	ASTM D5185m	0	5	2	47
The BN result indicates that there is suitable alkalinity remaining in the oil. Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.	Barium	ppm	ASTM D5185m		0	0	0
	Molybdenum	ppm	ASTM D5185m		45	44	16
	Manganese	ppm	ASTM D5185m		<1	<1	<1
	Magnesium	ppm	ASTM D5185m		855	807	711
	Calcium	ppm	ASTM D5185m		1024	1005	1080
	Phosphorus	ppm	ASTM D5185m	1150	938	889	697
	Zinc	ppm	ASTM D5185m		1139	1049	815
	Sulfur	ppm	ASTM D5185m	2060	3269	3016	2890
	Oxidation	Abs/.1mm	*ASTM D7414	>25	22.0	18.3	16.2
	Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.5	8.0	7.5







Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : GFL0118201 Lab Number : 06224357

Received **Tested** Diagnosed Unique Number : 11102554

Test Package: FLEET (Additional Tests: PercentFuel)

: 02 Jul 2024 : 02 Jul 2024 - Wes Davis

: 01 Jul 2024

2120 West Bennett Street Springfield, MO US 65807

GFL Environmental - 822 - Springfield Hauling

Contact: Dennis Moore dennis.moore@gflenv.com T: (417)403-3641

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)