

## JOHN DEERE 850L 1T0850LXVPF452697 Component Right Inner Final Drive

{not provided} (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

## **WEAR**

All component wear rates are normal.

\_\_\_\_\_

## CONTAMINATION


There is no indication of any contamination in the oil.


## **FLUID CONDITION**


The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0223125		
Sample Date		Client Info		30 Jun 2024		
Machine Age	hrs	Client Info		796		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Filter Changed		Client Info		N/A		
Sample Status				NORMAL		
PQ		ASTM D8184	>1250	45		
Iron	ppm	ASTM D5185m	>750	65		
Chromium	ppm	ASTM D5185m	>9	<1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>40	2		
Lead	ppm	ASTM D5185m	>15	1		
Copper	ppm	ASTM D5185m	>40	<1		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		<1		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>75	6		
Potassium	ppm	ASTM D5185m	>20	2		
Water	ppin	WC Method	>0.075	- NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.075	NEG		
Sodium	ppm	ASTM D5185m	>51	1		
Boron	ppm	ASTM D5185m		<1		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		1		
Magnesium	ppm	ASTM D5185m		97		
Calcium	ppm	ASTM D5185m		3596		
Phosphorus	ppm	ASTM D5185m		1081		
Zinc	ppm	ASTM D5185m		1332		
Sulfur	ppm	ASTM D5185m		4031		
Visc @ 40°C	cSt	ASTM D445		50.8		

Contact/Location: NICK GALLAHER - JAMGRE







Contact/Location: NICK GALLAHER - JAMGRE Page 2 of 2