

Machine Id

JOHN DEERE 4038R 1N04038RCE0001887

Rear Right Hub

JOHN DEERE GL-5 80W90 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0172275		
	Sample Date		Client Info		27 Jun 2024		
	Machine Age	hrs	Client Info		1515		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		65		
Metal levels are typical for a new component breaking in.	Iron	ppm	ASTM D5185m		238		
	Chromium	ppm	ASTM D5185m		5		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		2		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m		3		
	Lead	ppm	ASTM D5185m		2		
	Copper	ppm	ASTM D5185m		95		
	Tin	ppm	ASTM D5185m		2		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	MODER		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		9		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	6		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		42		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		46		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		2		
	Molybdenum	ppm	ASTM D5185m		1		
	Manganese	ppm	ASTM D5185m		7		
	Magnesium	ppm	ASTM D5185m		14		
	Calcium	ppm	ASTM D5185m		226		
	Phosphorus	ppm	ASTM D5185m		892		
	Zinc	ppm	ASTM D5185m		122		
	Sulfur	ppm	ASTM D5185m		17128		
		PP/11					


Visc @ 40°C


ASTM D445


cSt

Contact/Location: BILL ACKER - JAMWAK

113







Contact/Location: BILL ACKER - JAMWAK Page 2 of 2