



| | |
|-----------------|---------------|
| WEAR | NORMAL |
| CONTAMINATION | NORMAL |
| FLUID CONDITION | NORMAL |

Area
CRAIG E PHILIP
Machine Id
[CRAIG E PHILIP] 002 565024-2
Component
Center Main Engine
Fluid
CHEVRON DELO 710 LE (235 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

| Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|----------------|-----|-------------|-----------|--------------------|-------------|-------------|
| Sample Number | | Client Info | | MW0068807 | MW0064708 | MW0061334 |
| Sample Date | | Client Info | | 01 Jun 2024 | 01 Mar 2024 | 07 Feb 2024 |
| Machine Age | hrs | Client Info | | 24210 | 23402 | 22867 |
| Oil Age | hrs | Client Info | | 1346 | 538 | 3 |
| Filter Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | Not Changd | N/A | N/A |
| Filter Changed | | Client Info | | None | N/A | N/A |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |

WEAR

All component wear rates are normal.

| | | | | | | |
|--------------|--------|-------------|------|-------------|------|------|
| Iron | ppm | ASTM D5185m | >75 | 32 | 21 | 9 |
| Chromium | ppm | ASTM D5185m | >8 | 0 | <1 | 0 |
| Nickel | ppm | ASTM D5185m | >2 | 0 | <1 | 0 |
| Titanium | ppm | ASTM D5185m | >3 | 0 | <1 | 0 |
| Silver | ppm | ASTM D5185m | >2 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >15 | 2 | 3 | 2 |
| Lead | ppm | ASTM D5185m | >18 | 10 | 10 | 6 |
| Copper | ppm | ASTM D5185m | >80 | 12 | 10 | 2 |
| Tin | ppm | ASTM D5185m | >14 | 4 | 4 | <1 |
| Vanadium | ppm | ASTM D5185m | | 0 | <1 | 0 |
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |

CONTAMINATION








There is no indication of any contamination in the oil.

| | | | | | | |
|------------------|----------|-------------|-------|----------------|-------|-------|
| Silicon | ppm | ASTM D5185m | >20 | 5 | 5 | 6 |
| Potassium | ppm | ASTM D5185m | >20 | <1 | 0 | 0 |
| Fuel | | WC Method | >4.0 | <1.0 | <1.0 | <1.0 |
| Water | | WC Method | >0.1 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| Soot % | % | *ASTM D7844 | >3 | 0.1 | 0.1 | 0.1 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 8.4 | 6.8 | 4.4 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 15.4 | 14.1 | 13.1 |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.1 | NEG | NEG | NEG |

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| | | | | | | |
|------------------|----------|-------------|------|--------------|------|------|
| Sodium | ppm | ASTM D5185m | >75 | 16 | 4 | 3 |
| Boron | ppm | ASTM D5185m | | 36 | 40 | 40 |
| Barium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | | 45 | 44 | 42 |
| Manganese | ppm | ASTM D5185m | | <1 | <1 | 0 |
| Magnesium | ppm | ASTM D5185m | | 10 | 30 | 34 |
| Calcium | ppm | ASTM D5185m | | 3479 | 3348 | 3072 |
| Phosphorus | ppm | ASTM D5185m | | 4 | 23 | 16 |
| Zinc | ppm | ASTM D5185m | 10 | <1 | 32 | 17 |
| Sulfur | ppm | ASTM D5185m | | 2623 | 2641 | 2121 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 9.1 | 7.7 | 5.9 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 9.2 | 9.21 | 9.62 | 9.82 |
| Visc @ 100°C | cSt | ASTM D445 | 15.5 | 14.6 | 14.3 | 14.9 |



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW0068807

Lab Number : 06225344

Unique Number : 11103541

Test Package : MAR 2

Received : 01 Jul 2024

Tested : 02 Jul 2024

Diagnosed : 02 Jul 2024 - Wes Davis

INGRAM BARGE

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: ANTHONY VAN CURA

anthony.vancura@ingrambarga.com

T: (270)415-4467

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)