

Machine Id

JOHN DEERE 210P 1FF210PAVPF001078

Right Final Drive

JOHN DEERE GL-5 80W90 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0222601		
	Sample Date		Client Info		26 Jun 2024		
	Machine Age	hrs	Client Info		460		
	Oil Age	hrs	Client Info		460		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		None		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		180		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>500	246		
	Chromium	ppm	ASTM D5185m	>10	4		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>25	6		
	Lead	ppm	ASTM D5185m	>25	<1		
	Copper	ppm	ASTM D5185m	>50	1		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		71		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		4		
	Water			>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
	Boron	ppm	ASTM D5185m		68		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		5		
	Molybdenum	ppm	ASTM D5185m		3		
	Manganese	ppm	ASTM D5185m		6		
	Magnesium	ppm	ASTM D5185m		2		
		PPIII					
	-	nnm	ASTM D5185m		87		
	Calcium	ppm	ASTM D5185m		87 521		
	-	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m		87 521 44		

Sulfur

Visc @ 40°C


ppm ASTM D5185m

ASTM D445


cSt

188 --- ---Submitted By: JOHN GUASCHINO

13593







Submitted By: JOHN GUASCHINO Page 2 of 2