



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
QUEEN CITY
Component
Starboard Main Engine
Fluid
CHEVRON DELO 710 LS (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0062679	MW0062654	MW0062650
Sample Date		Client Info		30 Apr 2024	01 Apr 2024	29 Feb 2024
Machine Age	hrs	Client Info		14934	14241	13473
Oil Age	hrs	Client Info		276	14241	500
Filter Age	hrs	Client Info		534	1492	500
Oil Changed		Client Info		Not Chngd	N/A	Not Chngd
Filter Changed		Client Info		Not Chngd	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	8	13	11
Chromium	ppm	ASTM D5185m	>8	0	0	<1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	2	1	2
Lead	ppm	ASTM D5185m	>18	<1	<1	2
Copper	ppm	ASTM D5185m	>80	4	8	7
Tin	ppm	ASTM D5185m	>14	<1	2	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>20	2	2	3
Potassium	ppm	ASTM D5185m	>20	<1	<1	2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.4	0.7	0.5
Nitration	Abs/cm	*ASTM D7624	>20	5.3	6.2	5.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	13.8	14.6	14.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	2	8	18
Boron	ppm	ASTM D5185m		38	39	46
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		40	42	46
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m		0	33	36
Calcium	ppm	ASTM D5185m		3084	3336	3405
Phosphorus	ppm	ASTM D5185m		0	8	20
Zinc	ppm	ASTM D5185m		0	5	29
Sulfur	ppm	ASTM D5185m		2155	2499	2678
Oxidation	Abs/.1mm	*ASTM D7414	>25	6.0	6.4	6.2
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	5.8	6.8	6.6
Visc @ 100°C	cSt	ASTM D445	15.5	14.6	14.6	14.4


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Acid Number




Viscosity @ 40°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Acid Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW0062679

Lab Number : 06225617

Unique Number : 11103814

Test Package : MAR 2 (Additional Tests: KV40, TAN Man)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Received : 01 Jul 2024

Tested : 03 Jul 2024

Diagnosed : 03 Jul 2024 - Jonathan Hester

C & B MARINE

50 E RIVERCENTER BLVD, SUITE 1180

COVINGTON, KY

US 41011

Contact: DAVID WESTRICH

dwestrich@carlislebray.com

T: (812)290-4063

F: (859)655-7504