

WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL

Machine Id

24F2103 SLLCE-005

Component New (Unused) Oil Fluid

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		HPL0005258		
This is a baseline read-out on the submitted sample.	Sample Date		Client Info		24 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		0		
	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		0		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Ciliana		ACTM DE10E				
	Silicon	ppm	ASTM D5185m	00	0		
	Potassium	ppm	ASTM D5185m	>20	0		
	Water		WC Method	5000	NEG		
	Particles >4µm		ASTM D7647		34		
	Particles >6µm		ASTM D7647		13		
	Particles >14µm		ASTM D7647		2		
	Particles >21µm		ASTM D7647		1		
	Particles >38µm		ASTM D7647		0		
	Particles >71µm		ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		12/11/9		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual		NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		0		
	Calcium	ppm	ASTM D5185m		0		
	Phosphorus	ppm	ASTM D5185m		<1		
	Zinc	ppm	ASTM D5185m		0		
	Sulfur	ppm	ASTM D5185m		1944		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.077		
	Visc @ 40°C	cSt	ASTM D445		17.44		
	Visc @ 100°C	cSt	ASTM D445		4.37		
	Viscosity Index (VI)				170		





Certificate L2367

Laboratory Sample No. Unique Number: 11103894

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : HPL0005258 Lab Number : 06225697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received : 01 Jul 2024 **Tested** Diagnosed

: 03 Jul 2024 : 03 Jul 2024 - Jonathan Hester

HIGH PERFORMANCE LUBRICANTS LLC 500 S SPRUCE ST MANTENO, IL

US 60950 Contact: DAVID WARD

sampledata@hplubricants.com T: (815)468-3535

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Test Package: MOB 2 (Additional Tests: FT-IR, KV100, PrtCount, VI)

F: x: