



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE E234
 Component
Diesel Engine
 Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0219633	JR0171146	JR0118719
Sample Date		Client Info		18 Jun 2024	19 Jun 2023	18 Mar 2022
Machine Age	hrs	Client Info		1526	1005	488
Oil Age	hrs	Client Info		521	517	488
Filter Age	hrs	Client Info		521	517	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	12	19	20
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	<1	<1
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	6	9	4
Lead	ppm	ASTM D5185m	>40	2	6	4
Copper	ppm	ASTM D5185m	>330	4	22	119
Tin	ppm	ASTM D5185m	>15	<1	2	2
Vanadium	ppm	ASTM D5185m		<1	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION









There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	8	9	8
Potassium	ppm	ASTM D5185m	>20	3	2	0
Fuel		WC Method	>5	<1.0	<1.0	0.4
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	8.9	9.3	9.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.4	25.2	24.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	3	3
Boron	ppm	ASTM D5185m		203	196	256
Barium	ppm	ASTM D5185m		2	<1	0
Molybdenum	ppm	ASTM D5185m		265	282	241
Manganese	ppm	ASTM D5185m		<1	3	4
Magnesium	ppm	ASTM D5185m		794	924	840
Calcium	ppm	ASTM D5185m		1411	1620	1533
Phosphorus	ppm	ASTM D5185m		830	878	866
Zinc	ppm	ASTM D5185m		1053	1116	1030
Sulfur	ppm	ASTM D5185m		2639	3733	2496
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.5	20.1	18.3
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.2	7.6	9.8
Visc @ 100°C	cSt	ASTM D445	15.4	13.5	13.2	11.0



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0219633 **Received** : 02 Jul 2024
Lab Number : 06225822 **Tested** : 03 Jul 2024
Unique Number : 11109315 **Diagnosed** : 03 Jul 2024 - Jonathan Hester
Test Package : CONST (Additional Tests: KV40, TBN)

MATTHEWS CONSTRUCTION
 127 GRAYSON RD
 ROCK HILL, SC
 US 29732
 Contact: Tad Clinton
 tclinton@matthewsconstructionco.com
 T: (803)207-5607
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)