



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area

**MONTGOMERY**

Machine Id

**MACK 925034-152592**

Component

**Diesel Engine**

Fluid

**PETRO CANADA DURON SHP 15W40 (--- LTR)**



**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0127771</b>	GFL0088022	GFL0118433
Sample Date		Client Info		<b>28 Jun 2024</b>	23 May 2024	06 May 2024
Machine Age	hrs	Client Info		<b>24748</b>	24498	24361
Oil Age	hrs	Client Info		<b>24748</b>	24498	24361
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>N/A</b>	Not Changd	N/A
Filter Changed		Client Info		<b>N/A</b>	Not Changd	N/A
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	<b>4</b>	6	5
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	<1	<1
Nickel	ppm	ASTM D5185m	>5	<b>&lt;1</b>	<1	<1
Titanium	ppm	ASTM D5185m	>2	<b>&lt;1</b>	<1	<1
Silver	ppm	ASTM D5185m	>2	<b>&lt;1</b>	1	0
Aluminum	ppm	ASTM D5185m	>20	<b>3</b>	3	2
Lead	ppm	ASTM D5185m	>40	<b>&lt;1</b>	1	1
Copper	ppm	ASTM D5185m	>330	<b>&lt;1</b>	2	1
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	1	1
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>4</b>	6	5
Potassium	ppm	ASTM D5185m	>20	<b>2</b>	3	3
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>4	<b>0.1</b>	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	<b>5.5</b>	7.5	6.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>17.7</b>	18.1	18.2
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>2</b>	6	2
Boron	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	<1
Barium	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	0
Molybdenum	ppm	ASTM D5185m	60	<b>63</b>	60	54
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185m	1010	<b>902</b>	963	883
Calcium	ppm	ASTM D5185m	1070	<b>1045</b>	1082	1007
Phosphorus	ppm	ASTM D5185m	1150	<b>946</b>	1038	970
Zinc	ppm	ASTM D5185m	1270	<b>1151</b>	1250	1166
Sulfur	ppm	ASTM D5185m	2060	<b>2602</b>	3292	3260
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>13.5</b>	14.8	14.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>8.5</b>	8.0	8.5
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.8</b>	13.5	13.7



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0127771  
**Lab Number** : 06226010  
**Unique Number** : 11109503  
**Test Package** : FLEET

**Received** : 02 Jul 2024  
**Tested** : 03 Jul 2024  
**Diagnosed** : 03 Jul 2024 - Wes Davis

**GFL Environmental - 955 - Montgomery**  
 1121 Wilbanks St  
 Montgomery, AL  
 US 36108  
 Contact: LISA REEVES

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: