



WEAR CHECK

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id

104

Component

Diesel Engine

Fluid

DIESEL ENGINE OIL SAE 10W30 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0827662	WC0827735	WC0691265
Sample Date		Client Info		25 Jun 2024	17 Nov 2023	23 Jun 2023
Machine Age	mls	Client Info		137508	111680	82869
Oil Age	mls	Client Info		5348	29166	32984
Filter Age	mls	Client Info		5348	29166	32984
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	14	17	31
Chromium	ppm	ASTM D5185m	>20	1	2	2
Nickel	ppm	ASTM D5185m	>4	<1	<1	<1
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	<1	<1	0
Aluminum	ppm	ASTM D5185m	>20	4	2	8
Lead	ppm	ASTM D5185m	>40	2	2	3
Copper	ppm	ASTM D5185m	>330	2	4	4
Tin	ppm	ASTM D5185m	>15	1	2	1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	7	8
Potassium	ppm	ASTM D5185m	>20	9	8	15
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.4
Nitration	Abs/cm	*ASTM D7624	>20	8.5	8.8	10.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	21.4	24.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	0	0
Boron	ppm	ASTM D5185m	250	17	36	17
Barium	ppm	ASTM D5185m	10	<1	0	0
Molybdenum	ppm	ASTM D5185m	100	67	63	55
Manganese	ppm	ASTM D5185m		<1	1	1
Magnesium	ppm	ASTM D5185m	450	731	381	310
Calcium	ppm	ASTM D5185m	3000	1372	1889	1938
Phosphorus	ppm	ASTM D5185m	1150	959	989	1002
Zinc	ppm	ASTM D5185m	1350	1187	1243	1235
Sulfur	ppm	ASTM D5185m	4250	2653	3377	3459
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.3	16.9	18.9
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	7.7	6.5	5.3
Visc @ 100°C	cSt	ASTM D445	10.9	11.6	13.2	13.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : WC0827662

Lab Number : 06226027

Unique Number : 11109520

Test Package : FLEET

Received : 02 Jul 2024

Tested : 03 Jul 2024

Diagnosed : 03 Jul 2024 - Wes Davis

CARCO TRANSPORTATION

415 S WESTERN AVENUE

OKLAHOMA CITY, OK

US 73109

Contact: VICTOR STACHONIAK

victors@carcotrans.com

T: (405)239-2555

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)