

## DAVE DAVENPORT [6748] TWIN DISC MG-3050-A 6KH367 - INBOARD Component Port Gearbox

{not provided} (--- QTS)

## RECOMMENDATION

We recommend that you drain the oil from the component if this has not already been done. We advise that you inspect for the source(s) of wear. We recommend an early resample to monitor this condition.

### WEAR

Clutch wear is indicated.

#### CONTAMINATION


There is no indication of any contamination in the oil.


# FLUID CONDITION

The oil is no longer serviceable as a result of the abnormal and/or severe wear.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VPA052771		
Sample Date		Client Info		28 Jun 2024		
Machine Age	hrs	Client Info		1502		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		Not Changd		
Sample Status				SEVERE		
PQ		ASTM D8184		89		
Iron	nnm	ASTM D0104 ASTM D5185m	>200	09 111		
Chromium	ppm		>200			
	ppm	ASTM D5185m		<1 0		
Nickel	ppm	ASTM D5185m	>10	-		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	05	<1		
Aluminum	ppm	ASTM D5185m	>25	3		
Lead	ppm	ASTM D5185m	>50	▲ 650		
Copper	ppm	ASTM D5185m	>200	<b>3</b> 41		
Tin	ppm	ASTM D5185m	>10	1		
Vanadium	ppm	ASTM D5185m		0		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>50	3		
Potassium	ppm	ASTM D5185m	>20	1		
Water		WC Method	>0.2	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
0				• • • • • • • • • • • • • • • • • • • •		
Sodium	ppm	ASTM D5185m		0		
Boron	ppm	ASTM D5185m		34		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		21		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		3		
Calcium	ppm	ASTM D5185m		2761		
Phosphorus	ppm	ASTM D5185m		1169		
Zinc	ppm	ASTM D5185m		1258		
Sulfur	ppm	ASTM D5185m		4964		
Visc @ 40°C	cSt	ASTM D445		122		

Contact/Location: BRANDON ROBERTSON - VP759009





Contact/Location: BRANDON ROBERTSON - VP759009