WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Area

[W02008498]

VOLVO A30G 752473


Bogie/Center Axle


GEAR OIL SAE 80W140 (11 GAL)


GEAR OIL SAE 80W140 (11 GA	_)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. (Customer Sample	Sample Number		Client Info		ML0002356		
Comment: W02008498)	Sample Date		Client Info		01 Jul 2024		
	Machine Age	hrs	Client Info		3771		
	Oil Age	hrs	Client Info		3771		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAD			40TH DE 10E				
WEAR	Iron	ppm	ASTM D5185m		78		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	0.0	0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		4		
	Tin	ppm	ASTM D5185m	>20	<1		
	Vanadium	ppm	ASTM D5185m	NONE	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	2		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2		
There is no indication of any contamination in the oil.	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	nnm	ASTM D5185m		1		
	Boron	ppm	ASTM D5185m	400	171		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m	12	3		
	Magnesium	ppm	ASTM D5185m	12	3		
	Calcium	ppm	ASTM D5185m		109		
	Phosphorus	ppm	ASTM D5185m		1118		
	Zinc	ppm	ASTM D5185m		46		
	Sulfur	ppm	ASTM D5185m		34913		
	Visc @ 40°C	cSt	ASTM D445		282		
			-		. /		

Submitted By: DARRELL ANDES











Certificate L2367

Laboratory

Sample No.

: ML0002356 Lab Number : 06226824 Unique Number : 11110317 Test Package : CONST

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 02 Jul 2024

Tested : 03 Jul 2024 Diagnosed : 05 Jul 2024 - Don Baldridge **WILLIAM HAZEL** PO BOX 600 CHANTILLY, VA US 20153

Contact: SERVICE MANAGER jimmy_elswick@wahazel.com T: (703)378-8300

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: