**WEAR CONTAMINATION FLUID CONDITION**  **NORMAL NORMAL NORMAL** 


Machine Id

## NOT GIVEN WC0840313 (S/N NO INFO ON SIF/BOTTLE)

Diesel Engine

MOBIL DELVAC 1300 SUPER 15W40 (--- GAL)

ECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History
Resample at the next service interval to monitor.  WEAR	Sample Number		Client Info		WC0840313		
	Sample Date		Client Info		19 Mar 2024		
	Machine Age	hrs	Client Info		8994		
	Oil Age	hrs	Client Info		453		
	Filter Age	hrs	Client Info		453		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
	Iron	ppm	ASTM D5185m	>100	32		
	Chromium	ppm	ASTM D5185m		<1		
All component wear rates are normal.	Nickel		ASTM D5185m		1		
	Titanium	ppm	ASTM D5185m	24	0		
	Silver		ASTM D5185m	~3	0		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m	-	14		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m	710	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
<u></u>			Visuai	NONE			
ONTAMINATION	Silicon	ppm	ASTM D5185m	>25	7		
	Potassium	ppm	ASTM D5185m	>20	3		
There is no indication of any contamination in the oil.	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.3		
	Nitration	Abs/cm	*ASTM D7624	>20	10.5		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	19.5		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG		
LUD CONDITION	Codium		ACTM DE10Em		<b>7</b>		
LUID CONDITION	Sodium	ppm	ASTM D5185m	0	7 77		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Boron Barium	ppm	ASTM D5185m ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		105		
	Manganese	ppm	ASTM D5185m	U	2		
	Magnesium	ppm	ASTM D5185m	0	640		
	Calcium	ppm	ASTM D5185m	U	1294		
	Phosphorus	ppm	ASTM D5185m		773		
	Zinc	ppm	ASTM D5105m		865		
	Sulfur	ppm	ASTM D5185m		3592		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	16.8		
	Base Number (BN)		ASTM D2896		6.3		







Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0840313 Lab Number : 06227212

Unique Number : 11110705

Received **Tested** Test Package : CONST ( Additional Tests: KV40, TBN )

: 05 Jul 2024 Diagnosed : 05 Jul 2024 - Angela Borella

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: 03 Jul 2024

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

THE BAYOU COMPANY LLC

5200 CURTIS LN NEW IBERIA, LA US 70560

F: (337)365-9747

Contact: LES BORDELON lesb@bayoucompanies.com T: (800)619-4807