



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
2306
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 5W30 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		HRE0000665	WC0814843	WC0717419
Sample Date		Client Info		27 Jun 2024	22 Jul 2023	07 Oct 2022
Machine Age	mls	Client Info		320022	203435	104102
Oil Age	mls	Client Info		50000	100000	100000
Filter Age	mls	Client Info		50000	100000	50000
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	69	64	90
Chromium	ppm	ASTM D5185m	>20	<1	<1	1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	<1	<1	<1
Aluminum	ppm	ASTM D5185m	>20	7	11	27
Lead	ppm	ASTM D5185m	>40	0	0	<1
Copper	ppm	ASTM D5185m	>330	4	6	17
Tin	ppm	ASTM D5185m	>15	<1	1	3
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	22	13	17
Potassium	ppm	ASTM D5185m	>20	11	22	76
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1.1	0.8	0.7
Nitration	Abs/cm	*ASTM D7624	>20	15.4	14.5	15.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	33.0	29.8	33.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		7	6	5
Boron	ppm	ASTM D5185m	250	11	22	15
Barium	ppm	ASTM D5185m	10	0	0	<1
Molybdenum	ppm	ASTM D5185m	100	74	70	26
Manganese	ppm	ASTM D5185m		1	1	2
Magnesium	ppm	ASTM D5185m	450	1206	1254	926
Calcium	ppm	ASTM D5185m	3000	961	1024	1301
Phosphorus	ppm	ASTM D5185m	1150	1184	1170	882
Zinc	ppm	ASTM D5185m	1350	1435	1456	1087
Sulfur	ppm	ASTM D5185m	4250	3581	3957	3603
Oxidation	Abs/.1mm	*ASTM D7414	>25	36.6	31.0	32.8
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	3.0	5.0	5.1
Visc @ 100°C	cSt	ASTM D445	10.9	12.5	12.7	13.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : HRE0000665
Lab Number : 06227236
Unique Number : 11110729
Test Package : FLEET
Received : 03 Jul 2024
Tested : 06 Jul 2024
Diagnosed : 06 Jul 2024 - Don Baldrige

MABE TRUCKING
 PO BOX 1081
 EDEN, NC
 US 27289

Contact: MAINTENANCE
 maintenancemanager@mabetrucking.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (336)635-1791