

Machine Id JOHN DEERE 460P 1DW460PACRFB08088 Component **Center Differential**

JOHN DEERE HY-GARD HYD/TRANS (--- QTS)


	13)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		WE0007906	WE0006889	
	Sample Date		Client Info		01 Jul 2024	09 Apr 2024	
	Machine Age	hrs	Client Info		966	425	
	Oil Age	hrs	Client Info		966	425	
	Filter Age	hrs	Client Info		966	425	
	Oil Changed		Client Info		Not Changd	Changed	
	Filter Changed		Client Info		Not Changd	Not Changd	
	Sample Status				NORMAL	NORMAL	
WEAR	PQ		ASTM D8184		10	45	
WEAN		000		. 500	19 20		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		30	35	
	Chromium	ppm	ASTM D5185m		0	<1	
	Nickel	ppm	ASTM D5185m ASTM D5185m	>10		<1	
	Titanium Silver	ppm			0	<1	
	Aluminum	ppm	ASTM D5185m ASTM D5185m	- 25	0 <1	0	
	Lead	ppm	ASTM D5185m		15	8	
	Copper	ppm	ASTM D5185m		35	20	
	Tin	ppm	ASTM D5185m		3	3	
	Vanadium	ppm ppm	ASTM D5185m	>10	0	<1	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
			violai				
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	5	7	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	<1	3	
	Water		WC Method	>.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		6	4	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	4	<1	
	Barium	ppm	ASTM D5185m	0	3	4	
	Molybdenum	ppm	ASTM D5185m	0	0	2	
	Manganese	ppm	ASTM D5185m		2	3	
	Magnesium	ppm	ASTM D5185m	145	103	100	
	Calcium	ppm	ASTM D5185m	3570	3519	3619	
	Phosphorus	ppm	ASTM D5185m	1290	1100	1149	
	Zinc	ppm	ASTM D5185m	1640	1241	1208	
	Sulfur	ppm	ASTM D5185m		4526	4010	
		<u>.</u>					


Visc @ 40°C


cSt

ASTM D445 57.0 49.5 Contact/Location: SCOTT GOOD - WARNOR

51.4







Contact/Location: SCOTT GOOD - WARNOR Page 2 of 2

ul1/24