

[232292] JOHN DEERE 1FF190GWCMF052117

Front Right Final Drive

JOHN DEERE HY-GARD HYDRAULIC/RANSMISSION (8 GAL)


RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. (Customer Sample Comment: 232292)	Sample Number		Client Info		WE0007687		
	Sample Date		Client Info		01 Jul 2024		
	Machine Age	hrs	Client Info		1207		
	Oil Age	hrs	Client Info		1207		
	Filter Age	hrs	Client Info		1207		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		None		
	Sample Status				NORMAL		
				4050			
WEAR	PQ		ASTM D8184		78		
Metal levels are typical for a new component breaking in.	Iron	ppm	ASTM D5185m		113		
	Chromium	ppm	ASTM D5185m		1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		64		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	10		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	<1		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
	Codium						
FLUID CONDITION	Sodium	ppm	ASTM D5185m	1 C<	22		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		83		
	Barium	ppm	ASTM D5185m		5		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		12		
	Calcium	ppm	ASTM D5185m		3044		
	Phosphorus	ppm	ASTM D5185m		1143		
	Zinc	ppm	ASTM D5185m		1329		
	Sulfur	ppm	ASTM D5185m		4434		


Visc @ 40°C


cSt

ASTM D445 59

53.9 Submitted By: BOBBY LUCKY







Submitted By: BOBBY LUCKY Page 2 of 2