



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 250G C215649 (S/N 1FF250GXVEE609128)
 Component
Diesel Engine
 Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0221791	JR0170325	JR0131078
Sample Date		Client Info		01 Jul 2024	11 Aug 2023	27 Jun 2022
Machine Age	hrs	Client Info		4402	4092	3952
Oil Age	hrs	Client Info		4092	0	0
Filter Age	hrs	Client Info		4092	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	44	▲ 52	30
Chromium	ppm	ASTM D5185m	>11	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	1	1	1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	2
Aluminum	ppm	ASTM D5185m	>31	5	5	3
Lead	ppm	ASTM D5185m	>26	0	<1	<1
Copper	ppm	ASTM D5185m	>26	0	1	<1
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	7	3	6
Potassium	ppm	ASTM D5185m	>20	2	3	<1
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	0.3	0.4
Nitration	Abs/cm	*ASTM D7624	>20	9.7	8.1	9.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8	19.8	22.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	3	0	2
Boron	ppm	ASTM D5185m		219	248	263
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		245	255	244
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		885	768	793
Calcium	ppm	ASTM D5185m		1477	1405	1452
Phosphorus	ppm	ASTM D5185m		945	883	870
Zinc	ppm	ASTM D5185m		1160	1084	1049
Sulfur	ppm	ASTM D5185m		3675	3396	3565
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.3	15.1	17.8
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	9.2	9.4	10.6
Visc @ 100°C	cSt	ASTM D445	15.4	13.8	13.5	14.0



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : JR0221791

Lab Number : 06228235

Unique Number : 11111728

Test Package : CONST (Additional Tests: TBN)

Received : 05 Jul 2024

Tested : 05 Jul 2024

Diagnosed : 05 Jul 2024 - Wes Davis

JRE - STEPHENSON

245 YARDMASTER COURT

STEPHENSON, VA

US 22656-1761

Contact: PHIL DAUGHERTY

pdaugherty@jamesriverequipment.com

T: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (540)693-2588