



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
946016-260297
 Component
Natural Gas Engine
 Fluid
PETRO CANADA DURON GEO LD 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0121751	GFL0106810	GFL0084729
Sample Date		Client Info		01 Jul 2024	13 Mar 2024	16 Jun 2023
Machine Age	hrs	Client Info		7153	6574	122905
Oil Age	hrs	Client Info		600	600	0
Filter Age	hrs	Client Info		600	600	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	27	37	10
Chromium	ppm	ASTM D5185m	>4	<1	0	<1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>9	2	1	1
Lead	ppm	ASTM D5185m	>30	0	0	<1
Copper	ppm	ASTM D5185m	>35	9	20	10
Tin	ppm	ASTM D5185m	>4	0	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	LIGHT	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>+100	3	10	16
Potassium	ppm	ASTM D5185m	>20	0	<1	1
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	9.9	10.4	7.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.5	18.3	19.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		10	7	6
Boron	ppm	ASTM D5185m	50	15	17	39
Barium	ppm	ASTM D5185m	5	0	0	10
Molybdenum	ppm	ASTM D5185m	50	53	50	46
Manganese	ppm	ASTM D5185m	0	1	<1	3
Magnesium	ppm	ASTM D5185m	560	566	618	793
Calcium	ppm	ASTM D5185m	1510	1695	1680	1265
Phosphorus	ppm	ASTM D5185m	780	690	838	745
Zinc	ppm	ASTM D5185m	870	855	1032	911
Sulfur	ppm	ASTM D5185m	2040	2407	3064	2867
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.5	17.7	16.5
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	5.7	9.8	9.8
Visc @ 100°C	cSt	ASTM D445	15.1	14.8	13.3	14.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0121751
Lab Number : 06228393
Unique Number : 11111886
Test Package : FLEET

Received : 05 Jul 2024
Tested : 08 Jul 2024
Diagnosed : 08 Jul 2024 - Wes Davis

GFL Environmental - 856 - Houston South
 8515 Highway 6 South
 Houston, TX
 US 77083
 Contact: Apolinar Zacarias
 pzacariascano@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: