



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

(40962HA)

Machine Id

826021-1022

Component

Diesel Engine

Fluid

PETRO CANADA DURON SHP 15W40 (--- LTR)



RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0112854	GFL0100097	GFL0100132
Sample Date		Client Info		03 Jul 2024	03 Apr 2024	04 Jan 2024
Machine Age	mls	Client Info		187684	135532	135532
Oil Age	mls	Client Info		133093	133093	133093
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	4	2	4
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>5	0	0	<1
Titanium	ppm	ASTM D5185m	>2	<1	<1	<1
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	<1	1	2
Lead	ppm	ASTM D5185m	>40	0	0	0
Copper	ppm	ASTM D5185m	>330	1	<1	<1
Tin	ppm	ASTM D5185m	>15	0	0	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	2	2	3
Potassium	ppm	ASTM D5185m	>20	0	<1	2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>4	0.3	0.2	0.1
Nitration	Abs/cm	*ASTM D7624	>20	9.0	6.5	6.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.5	18.2	18.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		6	2	<1
Boron	ppm	ASTM D5185m	0	6	5	4
Barium	ppm	ASTM D5185m	0	0	0	10
Molybdenum	ppm	ASTM D5185m	60	65	56	68
Manganese	ppm	ASTM D5185m	0	<1	0	0
Magnesium	ppm	ASTM D5185m	1010	955	966	1047
Calcium	ppm	ASTM D5185m	1070	1184	1144	1216
Phosphorus	ppm	ASTM D5185m	1150	971	1035	1272
Zinc	ppm	ASTM D5185m	1270	1143	1259	1362
Sulfur	ppm	ASTM D5185m	2060	3150	3801	4073
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.3	14.6	14.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.8	8.0	8.4
Visc @ 100°C	cSt	ASTM D445	15.4	14.3	14.1	14.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0112854
Lab Number : 06228403
Unique Number : 11111896
Test Package : FLEET

GFL Environmental - 659 - Mechanicsville
 8280 RICHFOOD RD
 Mechanicsville, VA
 US 23116
 Contact: Dwayne Oliver
 dwayneoliver@gflenv.com
 T:
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)