



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 310E 1DW310EXJPF716543
Component
Center Differential
Fluid
JOHN DEERE HY-GARD HYD/TRANS (30 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0225431	JR0211055	JR0192369
Sample Date		Client Info		03 Jul 2024	02 Mar 2024	13 Nov 2023
Machine Age	hrs	Client Info		2458	1952	1446
Oil Age	hrs	Client Info		0	1952	941
Filter Age	hrs	Client Info		0	500	0
Oil Changed		Client Info		Not Changed	Changed	N/A
Filter Changed		Client Info		Not Changed	Changed	N/A
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184		92	78	121
Iron	ppm	ASTM D5185m	>500	135	173	181
Chromium	ppm	ASTM D5185m	>10	1	1	1
Nickel	ppm	ASTM D5185m	>10	4	6	8
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		<1	<1	0
Aluminum	ppm	ASTM D5185m	>25	2	3	2
Lead	ppm	ASTM D5185m	>25	9	13	13
Copper	ppm	ASTM D5185m	>100	66	▲ 127	99
Tin	ppm	ASTM D5185m	>10	3	5	5
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	MODER	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	9	10	10
Potassium	ppm	ASTM D5185m	>20	0	3	0
Water		WC Method	>.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		6	8	8
Boron	ppm	ASTM D5185m	6	18	40	38
Barium	ppm	ASTM D5185m	0	1	0	<1
Molybdenum	ppm	ASTM D5185m	0	10	7	6
Manganese	ppm	ASTM D5185m		8	15	15
Magnesium	ppm	ASTM D5185m	145	127	98	102
Calcium	ppm	ASTM D5185m	3570	3717	3384	3476
Phosphorus	ppm	ASTM D5185m	1290	1117	1107	1070
Zinc	ppm	ASTM D5185m	1640	1288	1258	1299
Sulfur	ppm	ASTM D5185m		4085	4096	3412
Visc @ 40°C	cSt	ASTM D445	57.0	54.8	55.6	56.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0225431 **Received** : 05 Jul 2024
Lab Number : 06228916 **Tested** : 08 Jul 2024
Unique Number : 11112409 **Diagnosed** : 08 Jul 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

B & S SITE DEVELOPMENT
 7800 PINEY BRANCH LANE
 BRISTOW, VA
 US 20136
 Contact: DANNY HUFF
 dhuff@bandssite.com
 T: (540)270-3203
 F: (703)753-0605

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)