

**WEAR CONTAMINATION FLUID CONDITION**  **NORMAL NORMAL NORMAL** 


[W02008502]


## **VOLVO EC480E 310963**

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the	Sample Number		Client Info		ML0002360		
brand, type, and viscosity of the oil on your next sample. ( Customer Sample Comment: W02008502 )	Sample Date		Client Info		03 Jul 2024		
	Machine Age	hrs	Client Info		9174		
	Oil Age	hrs	Client Info		9174		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
VEAD							
/EAR	Iron	ppm	ASTM D5185m		677		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		8		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>25	4		
	Lead	ppm	ASTM D5185m	>50	<1		
	Copper	ppm	ASTM D5185m	>50	13		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	0:1:		AOTA DEADE	400			
There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>100	22		
	Potassium	ppm	ASTM D5185m		3		
	Water		WC Method	>0.25	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.25	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		2		
	Boron	ppm	ASTM D5185m		113		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		7		
	Manganese	ppm	ASTM D5185m		7		
	Magnesium	ppm	ASTM D5185m		38		
	Calcium		ASTM D5185m		75		
		ppm	ASTM D5185m		880		
	Phosphorus	ppm					
	Zinc	ppm	ASTM D5185m		87		
	Sulfur	ppm	ASTM D5185m		25154		











Certificate L2367

Laboratory Sample No.

: ML0002360 Lab Number : 06229337 Unique Number : 11112830 Test Package : CONST

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** 

: 05 Jul 2024 : 09 Jul 2024 Diagnosed

: 09 Jul 2024 - Don Baldridge

**WILLIAM HAZEL** PO BOX 600 CHANTILLY, VA US 20153

Contact: SERVICE MANAGER jimmy\_elswick@wahazel.com T: (703)378-8300

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: