



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
RUSSELL [RUSSELL]

Machine Id
2013657604

Component
Port Diesel Engine

Fluid
VOLVO PENTA SAE 15W40 (12 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VPA039839	VPA037949	VPA026693
Sample Date		Client Info		28 Jun 2024	27 Jan 2022	28 Sep 2020
Machine Age	hrs	Client Info		928	473	347
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>80	8	6	7
Chromium	ppm	ASTM D5185m	>6	0	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	0	<1
Titanium	ppm	ASTM D5185m	>2	1	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	<1	4
Lead	ppm	ASTM D5185m	>95	0	<1	<1
Copper	ppm	ASTM D5185m	>85	1	2	2
Tin	ppm	ASTM D5185m	>9	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	LIGHT	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	6	7
Potassium	ppm	ASTM D5185m	>20	<1	<1	10
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.5	0.3	0.2
Nitration	Abs/cm	*ASTM D7624	>20	6.8	6.3	6.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	20.7	22.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	3	1
Boron	ppm	ASTM D5185m		201	35	292
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		83	66	106
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		560	964	609
Calcium	ppm	ASTM D5185m		1410	1114	1537
Phosphorus	ppm	ASTM D5185m		1036	1059	738
Zinc	ppm	ASTM D5185m		1250	1064	824
Sulfur	ppm	ASTM D5185m		3630	2629	2132
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.0	15.1	16.3
Base Number (BN)	mg KOH/g	ASTM D2896		7.2	10.4	---
Visc @ 100°C	cSt	ASTM D445		12.6	13.0	13.0



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VPA039839 **Received** : 05 Jul 2024
Lab Number : 06229369 **Tested** : 09 Jul 2024
Unique Number : 11112862 **Diagnosed** : 09 Jul 2024 - Jonathan Hester
Test Package : MOB 1 (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Suncoast Diesel Marine Inc.
 610 Mount Vernan St
 OLDSMAR, FL
 US 34677
 Contact: MARK WARREN
 oldsmar@suncoastdmi.com
 T: (813)475-5942
 F: (813)475-5943