WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

LOADER

Diesel Engine

CHEVRON 15W40 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History
Resample at the next service interval to monitor. Please specify the component make and model with your next sample.	Sample Number		Client Info		WE0007543		
	Sample Date		Client Info		22 Jun 2024		
	Machine Age	hrs	Client Info		500		
	Oil Age	hrs	Client Info		500		
	Filter Age	hrs	Client Info		500		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
/EAR	Iron	nnm	ASTM D5185m	> 100	48		
WLAN	Chromium	ppm	ASTM D5185m		2		
Metal levels are typical for a components first oil change.		ppm					
	Nickel	ppm	ASTM D5185m	>4	2		
	Titanium	ppm	ASTM D5185m		1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m		6		
	Lead	ppm	ASTM D5185m		2		
	Copper	ppm	ASTM D5185m		4		
	Tin	ppm	ASTM D5185m	>15	1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
ONTAMINATION	Silicon	ppm	ASTM D5185m	>25	12		
	Potassium	ppm	ASTM D5185m	>20	4		
There is no indication of any contamination in the oil.	Fuel		WC Method		<1.0		
	Water		WC Method		NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	1		
	Nitration	Abs/cm	*ASTM D7624	>20	10.6		
	Sulfation	Abs/.1mm	*ASTM D7415		26.0		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m	>50	5		
	Boron	ppm	ASTM D5185m		66		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		94		
	Manganese	ppm	ASTM D5185m		1		
	Magnesium	ppm	ASTM D5185m		421		
	Calcium	ppm	ASTM D5185m		1532		
	Phosphorus	ppm	ASTM D5185m		1117		
	Zinc	ppm	ASTM D5185m		1422		
	Sulfur	ppm	ASTM D5185m		3253		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	20.8		
	Base Number (BN)			720	6.0		
	Dase Mullipel (DIV)	my Romy	MO 1 IVI D2030		0.0		







Certificate L2367

Laboratory

Sample No.

Lab Number : 06229685

Unique Number : 11113178 Test Package : CONST (Additional Tests: TBN)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WE0007543 Received : 08 Jul 2024

Tested : 09 Jul 2024 Diagnosed

: 09 Jul 2024 - Wes Davis

WARRIOR TRACTOR AND EQUIPMENT - MONROEVILLE 66 INDUSTRIAL PARK DR MONROEVILLE, AL US 36460

Contact: SCOTT WILLIAMSON swilliamson@warriortractor.com T: (251)575-7111

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: