



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
D-93
 Component
Diesel Engine
 Fluid
PETRO CANADA 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0079180	PCA0061598	PCA0061607
Sample Date		Client Info		02 Jul 2024	03 Jan 2023	10 Aug 2022
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	26	8	31
Chromium	ppm	ASTM D5185m	>20	1	0	<1
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	3	0	3
Lead	ppm	ASTM D5185m	>40	2	<1	4
Copper	ppm	ASTM D5185m	>330	6	2	31
Tin	ppm	ASTM D5185m	>15	2	<1	3
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	7	5	▲ 59
Potassium	ppm	ASTM D5185m	>20	2	<1	3
Fuel		WC Method	>5	<1.0	<1.0	0.3
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.3	0.6
Nitration	Abs/cm	*ASTM D7624	>20	5.0	5.3	6.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.6	17.4	24.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	<1	0
Boron	ppm	ASTM D5185m		6	4	54
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		62	60	40
Manganese	ppm	ASTM D5185m		1	0	4
Magnesium	ppm	ASTM D5185m		1006	895	491
Calcium	ppm	ASTM D5185m		1176	1102	1617
Phosphorus	ppm	ASTM D5185m		1040	1029	929
Zinc	ppm	ASTM D5185m		1313	1181	1113
Sulfur	ppm	ASTM D5185m		3172	2523	2850
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.1	12.7	20.8
Base Number (BN)	mg KOH/g	ASTM D2896		9.6	9.4	11.6
Visc @ 100°C	cSt	ASTM D445		13.5	14.1	● 11.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0079180 **Received** : 08 Jul 2024
Lab Number : 06229697 **Tested** : 09 Jul 2024
Unique Number : 11113190 **Diagnosed** : 09 Jul 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

BORGAARD CONSTRUCTION
 70 CREEPER HILL RD
 NORTH GRAFTON, MA
 US 01536
 Contact: BILL PECKAM
 billpeckam@borggaard.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (508)839-9625