



VOLVO

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
VOLVO A40G 352909
Component
Diesel Engine
Fluid
VOLVO ULTRA DIESEL ENGINE OIL 15W40 VDS-3 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP454361	VCP443332	VCP437881
Sample Date		Client Info		02 Jul 2024	02 Jul 2024	01 Mar 2024
Machine Age	hrs	Client Info		1326	4610	4219
Oil Age	hrs	Client Info		0	0	500
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	10	4	8
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	3
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	2	5
Lead	ppm	ASTM D5185m	>40	<1	0	<1
Copper	ppm	ASTM D5185m	>330	40	5	2
Tin	ppm	ASTM D5185m	>15	1	0	1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION













There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	7	4	5
Potassium	ppm	ASTM D5185m	>20	2	1	2
Fuel	%	ASTM D3524	>6.0	<1.0	0.3	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.2	0.3
Nitration	Abs/cm	*ASTM D7624	>20	9.6	6.7	8.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.8	19.8	20.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	1	2
Boron	ppm	ASTM D5185m	2.5	25	48	27
Barium	ppm	ASTM D5185m	0.0	0	0	0
Molybdenum	ppm	ASTM D5185m	0.7	49	40	43
Manganese	ppm	ASTM D5185m	0.0	<1	0	<1
Magnesium	ppm	ASTM D5185m	256	452	555	565
Calcium	ppm	ASTM D5185m	2057	1825	1413	1568
Phosphorus	ppm	ASTM D5185m	935	962	901	926
Zinc	ppm	ASTM D5185m	1223	1149	1078	1108
Sulfur	ppm	ASTM D5185m	4079	3490	2771	3610
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.4	16.9	19.0
Base Number (BN)	mg KOH/g	ASTM D2896	10	7.8	9.9	9.1
Visc @ 100°C	cSt	ASTM D445	15.0	12.3	12.0	12.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : VCP454361

Lab Number : 06229791

Unique Number : 11113284

Test Package : MOB 1 (Additional Tests: FuelDilution, TBN)

Received : 08 Jul 2024

Tested : 09 Jul 2024

Diagnosed : 09 Jul 2024 - Sean Felton

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

ALTA EQUIPMENT COMPANY

5151 DR MARTIN LUTHER KING BLVD

FORT MYERS, FL

US 33905

Contact: TODD LARK

tlark@altaequipfl.com

T:

F: (239)481-3302