



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 310SK 1T0310SKPEE269065
Component
Diesel Engine
Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0220086	JRMC458412	JRMC425647
Sample Date		Client Info		02 Jul 2024	09 Mar 2018	26 May 2017
Machine Age	hrs	Client Info		1452	1452	927
Oil Age	hrs	Client Info		1452	500	500
Filter Age	hrs	Client Info		0	500	500
Oil Changed		Client Info		N/A	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	23	48	34
Chromium	ppm	ASTM D5185m	>11	1	2	<1
Nickel	ppm	ASTM D5185m	>5	1	0	0
Titanium	ppm	ASTM D5185m		1	<1	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>31	14	8	5
Lead	ppm	ASTM D5185m	>26	2	23	6
Copper	ppm	ASTM D5185m	>26	5	10	16
Tin	ppm	ASTM D5185m	>4	<1	0	10
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>22	9	8	4
Potassium	ppm	ASTM D5185m	>20	3	1	3
Fuel	%	ASTM D3524	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.8	1.2	0.8
Nitration	Abs/cm	*ASTM D7624	>20	7.5	9.	7.
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.4	25.	18.
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	2	4	5
Boron	ppm	ASTM D5185m		37	88	120
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		58	244	211
Manganese	ppm	ASTM D5185m		<1	1	1
Magnesium	ppm	ASTM D5185m		904	790	717
Calcium	ppm	ASTM D5185m		1133	1337	1462
Phosphorus	ppm	ASTM D5185m		967	766	738
Zinc	ppm	ASTM D5185m		1190	912	964
Sulfur	ppm	ASTM D5185m		3102	2538	2749
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.8	18.	13.
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	9.2	8.02	7.11
Visc @ 100°C	cSt	ASTM D445	15.4	12.5	14.92	15.08


FT-IR (Direct Trend)




Ferrous Alloys




Base Number




Non-ferrous Metals




Viscosity @ 100°C



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0220086 **Received** : 08 Jul 2024
Lab Number : 06229949 **Tested** : 09 Jul 2024
Unique Number : 11113442 **Diagnosed** : 09 Jul 2024 - Don Baldridge
Test Package : CONST (Additional Tests: FuelDilution, TBN)

JRE - CHARLOTTE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269

Contact: CHARLOTTE SHOP
 myoung@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (704)597-0211
 F: (704)596-6198