
**WEAR CONTAMINATION FLUID CONDITION**  **NORMAL NORMAL NORMAL** 

Machine Id

## **JOHN DEERE %2 744 P 1DW744PACNLX05964**

**Hydraulic System** 

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		JR0218891	JR0193466	
Resample at the next service interval to monitor.	Sample Date		Client Info		26 Jun 2024	05 Dec 2023	
	Machine Age	hrs	Client Info		1469	976	
	Oil Age	hrs	Client Info		1469	976	
	Filter Age	hrs	Client Info		1469	0	
	Oil Changed		Client Info		Not Changd	Not Changd	
	Filter Changed		Client Info		Not Changd	Not Changd	
	Sample Status				NORMAL	ATTENTION	
VEAR	PQ		ASTM D8184		17	19	
YEAR	Iron	ppm	ASTM D5185m	>20	6	6	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1	<1	
	Nickel	ppm	ASTM D5185m		0	<1	
	Titanium	ppm	ASTM D5185m	>10	0	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>10	<1	<1	
	Lead	ppm	ASTM D5185m		0	0	
	Copper		ASTM D5185m		2	2	
	Tin	ppm	ASTM D5185m		0	0	
	Vanadium	ppm	ASTM D5185m	>10	0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon		ACTM DE10Em	. 00		7	
		ppm	ASTM D5185m		6	7	
The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.	Potassium	ppm	ASTM D5185m		1	2	
	Water		WC Method		NEG	NEG	
	Particles >4µm		ASTM D7647		3894	7198	
	Particles >6µm		ASTM D7647		357	1945	
	Particles >14µm		ASTM D7647		20	155	
	Particles >21µm		ASTM D7647		3	39	
	Particles >38µm		ASTM D7647		0	1	
	Particles >71μm		ASTM D7647		0	1	
	Oil Cleanliness		ISO 4406 (c)		19/16/11	20/18/14	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
<u></u>	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
LUID CONDITION	Sodium	ppm	ASTM D5185m		4	1	
The AN level is acceptable for this fluid. The condition of the all in	Boron	ppm	ASTM D5185m		0	0	
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		0	<1	
	Manganese	ppm	ASTM D5185m		0	0	
	Magnesium	ppm	ASTM D5185m		0	2	
	Calcium	ppm	ASTM D5185m	87	82	97	
	Phosphorus	ppm	ASTM D5185m	727	600	653	
	Zinc	ppm	ASTM D5185m	900	729	839	
	Sulfur	ppm	ASTM D5185m	1500	1616	1523	
	Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.65	0.68	





Laboratory Sample No. Lab Number Unique Number : 11113551

: JR0218891

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 06230058

Received : 08 Jul 2024 **Tested** : 09 Jul 2024

: 09 Jul 2024 - Wes Davis Diagnosed

JRE - ASHEVILLE 101 BRUCE DRIVE ASHEVILLE, NC US 28806 Contact: Randy Warren

Test Package : CONST ( Additional Tests: PQ ) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

randy.warren@jamesriverequipment.com T: (528)667-0176

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: Mike Young - CHARLOTTE SHOP

F: (828)667-4865