

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL



Store 4 - Fairmont JOHN DEERE 210P 1FF210PAVPF000769

Right Propel Gearbox

JOHN DEERE GL-5 80W90 (2 GAL)


RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number	00111	Client Info	Liniorion	LEC0049805		
Resample at the next service interval to monitor.	Sample Date		Client Info		03 Jul 2024		
	Machine Age	hrs	Client Info		517		
	Oil Age	hrs	Client Info		517		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
			ASTM D8184		407		
WEAR All component wear rates are normal.	PQ			1050	107		
	Iron	ppm	ASTM D5185m		239		
	Chromium	ppm	ASTM D5185m		4		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium Silver	ppm	ASTM D5185m		<1		
		ppm	ASTM D5185m ASTM D5185m		0		
	Aluminum	ppm			<1		
	Lead	ppm	ASTM D5185m		<1 2		
	Copper Tin	ppm	ASTM D5185m ASTM D5185m		2		
	Vanadium	ppm	ASTM D5185m		0 <1		
		ppm					
	White Metal Yellow Metal	scalar	*Visual	NONE	NONE		
		scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m		21		
	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	MODER		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		63		
	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		6		
	Magnesium	ppm	ASTM D5185m		1		
	Calcium	ppm	ASTM D5185m		10		
	Phosphorus	ppm	ASTM D5185m		547		
	Zinc	ppm	ASTM D5185m		23		
	Sulfur	ppm	ASTM D5185m		18404		
	Vice @ 40°C	- 04			196		

Visc @ 40°C cSt


ASTM D445

Submitted By: JOHN MARTIN

186







Submitted By: JOHN MARTIN Page 2 of 2