

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



Machine Id **BELL B25E B93A625EC03009895**

Front Differential

GEAR OIL SAE 80W90 (7 GAL)

GEAR OIL SAE 80W90 (7 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		BE0002194		
nesample at the next service interval to monitor.	Sample Date		Client Info		01 Jul 2024		
	Machine Age	hrs	Client Info		2012		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>3000	62		
	Iron	ppm	ASTM D5185m	>HR:1=	416		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		3		
	Nickel	ppm	ASTM D5185m		2		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	6		
	Lead	ppm	ASTM D5185m	>25	<1		
	Copper	ppm	ASTM D5185m	>100	25		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>201	4		
	Potassium	ppm	ASTM D5185m		2		
There is no indication of any contamination in the oil.	Water	le le	WC Method	>1.01	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>1.01	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		- <1		
The condition of the on is acceptable for the time in service.	Barium	ppm	ASTM D5185m	200	0		
	Molybdenum	ppm	ASTM D5185m	12	<1		
	Manganese	ppm	ASTM D5185m		8		
	Magnesium	ppm	ASTM D5185m	12	2		
	Calcium	ppm	ASTM D5185m		38		
	Phosphorus	ppm	ASTM D5185m		1197		
	Zinc	ppm	ASTM D5185m		76		
	Sulfur	ppm	ASTM D5185m		32727		
Report Id: BENEW005 [WUSCAR] 06230486 (Generated: 07/10/2024 11:28:16) Rev: 1	Visc @ 40°C	cSt	ASTM D445	143	129	l Subr	mitted By: ?





Laboratory Sample No.

Lab Number : 06230486 Unique Number : 11113979 Test Package : MOBCE

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : BE0002194

Received : 08 Jul 2024 **Tested**

: 10 Jul 2024 Diagnosed

: 10 Jul 2024 - Don Baldridge

Newman Tractor 2841 Verona Road Verona, KY US 41092

Contact: Justin Newman justin@newmantractor.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (859)485-8500

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: