



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Area  
**KEMP QUARRIES / PRYOR STONE [70706]**  
Machine Id  
**OHT110**  
Component  
**Rear Left Final Drive**  
Fluid  
**PETRO CANADA PRODURO TO-4 SAE 50 (--- GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor. ( Customer Sample Comment: Pm1 performed. All oil samples taken. Engine oil, engine oil filters, fuel filters, and air filters changed. )

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>PCA0108871</b>	PCA0086624	PCA0086251
Sample Date		Client Info		<b>19 Jun 2024</b>	29 Mar 2024	26 Oct 2023
Machine Age	hrs	Client Info		<b>29710</b>	29240	28435
Oil Age	hrs	Client Info		<b>470</b>	2145	1340
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Oil Added</b>	Changed	Oil Added
Filter Changed		Client Info		<b>N/A</b>	N/A	N/A
Sample Status				<b>NORMAL</b>	ATTENTION	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>800	<b>13</b>	24	38
Chromium	ppm	ASTM D5185m	>10	<b>0</b>	<1	0
Nickel	ppm	ASTM D5185m	>5	<b>0</b>	<1	0
Titanium	ppm	ASTM D5185m	>15	<b>0</b>	<1	0
Silver	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>75	<b>1</b>	3	<1
Lead	ppm	ASTM D5185m	>10	<b>&lt;1</b>	<1	0
Copper	ppm	ASTM D5185m	>75	<b>2</b>	2	<1
Tin	ppm	ASTM D5185m	>8	<b>0</b>	<1	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	<1	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>400	<b>14</b>	8	17
Potassium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	1	0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		<b>2</b>	1	3
Boron	ppm	ASTM D5185m	2	<b>0</b>	0	0
Barium	ppm	ASTM D5185m	0	<b>0</b>	1	0
Molybdenum	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	0
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	0
Magnesium	ppm	ASTM D5185m	9	<b>16</b>	7	15
Calcium	ppm	ASTM D5185m	3114	<b>3454</b>	● 1290	3147
Phosphorus	ppm	ASTM D5185m	1099	<b>982</b>	● 589	984
Zinc	ppm	ASTM D5185m	1245	<b>1126</b>	● 753	1212
Sulfur	ppm	ASTM D5185m	7086	<b>4820</b>	● 2102	3917
Visc @ 40°C	cSt	ASTM D445	213.9	<b>176</b>	● 88.0	168



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : PCA0108871  
**Lab Number** : 06230642  
**Unique Number** : 11114135  
**Test Package** : MOB 1

**Received** : 08 Jul 2024  
**Tested** : 10 Jul 2024  
**Diagnosed** : 10 Jul 2024 - Jonathan Hester

**Kemp Quarries - Pryor Stone - Pryor**  
 1050 E 520 Rd  
 Pryor, OK  
 US 74361  
 Contact:  
 pryor@pryorstone.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: