



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
FREIGHTLINER 122040-SW8201
Component
Diesel Engine
Fluid
MOBIL DELVAC ELITE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0111316	GFL0095453	GFL0095474
Sample Date		Client Info		25 Apr 2024	30 Jan 2024	03 Jan 2024
Machine Age	hrs	Client Info		3386	2906	2760
Oil Age	hrs	Client Info		480	500	500
Filter Age	hrs	Client Info		0	500	500
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>80	5	2	6
Chromium	ppm	ASTM D5185m	>5	0	<1	0
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>30	5	4	5
Lead	ppm	ASTM D5185m	>30	<1	<1	0
Copper	ppm	ASTM D5185m	>150	28	17	32
Tin	ppm	ASTM D5185m	>5	2	1	3
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	3	3	3
Potassium	ppm	ASTM D5185m	>20	8	4	7
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	9.1	7.6	8.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.6	17.3	17.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	10	2
Boron	ppm	ASTM D5185m		89	122	91
Barium	ppm	ASTM D5185m		0	<1	2
Molybdenum	ppm	ASTM D5185m		130	118	118
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		701	629	673
Calcium	ppm	ASTM D5185m		1256	1135	1223
Phosphorus	ppm	ASTM D5185m		805	679	722
Zinc	ppm	ASTM D5185m		885	769	791
Sulfur	ppm	ASTM D5185m		3845	2917	3048
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.5	13.4	15.1
Base Number (BN)	mg KOH/g	ASTM D2896	10.7	6.2	7.1	6.1
Visc @ 100°C	cSt	ASTM D445	15.2	13.2	13.3	13.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0111316 **Received** : 09 Jul 2024
Lab Number : 06231190 **Tested** : 10 Jul 2024
Unique Number : 11114683 **Diagnosed** : 10 Jul 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 981 - Port Arthur Hauling
 1000 S Business Park Dr
 Port Arthur, TX
 US 77640
 Contact: MICHAEL KAY
 mkay@gflenv.com
 T: (336)660-9331
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)