



PacLease

# OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**PETERBILT 8271076**

Component  
**Diesel Engine**

Fluid  
**CHEVRON DELO 400 SAE 10W30 (44 QTS)**

## RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>RPL0004758</b>	---	---
Sample Date		Client Info		<b>25 Jun 2024</b>	---	---
Machine Age	mls	Client Info		<b>35517</b>	---	---
Oil Age	mls	Client Info		<b>35517</b>	---	---
Filter Age	mls	Client Info		<b>35517</b>	---	---
Oil Changed		Client Info		<b>Changed</b>	---	---
Filter Changed		Client Info		<b>Changed</b>	---	---
Sample Status				<b>NORMAL</b>	---	---

## WEAR

Metal levels are typical for a components first oil change.

Iron	ppm	ASTM D5185m	>100	<b>90</b>	---	---
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	---	---
Nickel	ppm	ASTM D5185m	>4	<b>0</b>	---	---
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	---	---
Silver	ppm	ASTM D5185m	>3	<b>&lt;1</b>	---	---
Aluminum	ppm	ASTM D5185m	>20	<b>53</b>	---	---
Lead	ppm	ASTM D5185m	>40	<b>&lt;1</b>	---	---
Copper	ppm	ASTM D5185m	>330	<b>16</b>	---	---
Tin	ppm	ASTM D5185m	>15	<b>2</b>	---	---
Vanadium	ppm	ASTM D5185m		<b>0</b>	---	---
White Metal	scalar	*Visual	NONE	<b>NONE</b>	---	---
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	---	---

## CONTAMINATION








Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>18</b>	---	---
Potassium	ppm	ASTM D5185m	>20	<b>173</b>	---	---
Fuel		WC Method	>5	<b>&lt;1.0</b>	---	---
Water		WC Method	>0.2	<b>NEG</b>	---	---
Glycol		WC Method		<b>NEG</b>	---	---
Soot %	%	*ASTM D7844	>3	<b>0.5</b>	---	---
Nitration	Abs/cm	*ASTM D7624	>20	<b>11.4</b>	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>26.5</b>	---	---
Silt	scalar	*Visual	NONE	<b>NONE</b>	---	---
Debris	scalar	*Visual	NONE	<b>NONE</b>	---	---
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	---	---
Appearance	scalar	*Visual	NORML	<b>NORML</b>	---	---
Odor	scalar	*Visual	NORML	<b>NORML</b>	---	---
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	---	---

## FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>6</b>	---	---
Boron	ppm	ASTM D5185m		<b>15</b>	---	---
Barium	ppm	ASTM D5185m		<b>0</b>	---	---
Molybdenum	ppm	ASTM D5185m		<b>4</b>	---	---
Manganese	ppm	ASTM D5185m		<b>3</b>	---	---
Magnesium	ppm	ASTM D5185m		<b>711</b>	---	---
Calcium	ppm	ASTM D5185m		<b>1634</b>	---	---
Phosphorus	ppm	ASTM D5185m	1260	<b>885</b>	---	---
Zinc	ppm	ASTM D5185m	1400	<b>986</b>	---	---
Sulfur	ppm	ASTM D5185m		<b>3929</b>	---	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>21.0</b>	---	---
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	<b>5.0</b>	---	---
Visc @ 100°C	cSt	ASTM D445	11.1	<b>11.9</b>	---	---



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513

**Sample No.** : RPL0004758

**Lab Number** : 06231234

**Unique Number** : 11114727

**Test Package** : FLEET

**Received** : 09 Jul 2024

**Tested** : 10 Jul 2024

**Diagnosed** : 10 Jul 2024 - Wes Davis

**RTL PACLEASE - 7009 - Nashville**

900 Expo Dr.

Smyrna, TN

US 37167

Contact: TECHNICIAN ACCOUNT

catherine.anastasio@wearcheck.com

T:

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)