WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL


Machine Id

PETERBILT 8591820

Diesel Engine

CHEVRON DELO 400 SAE 10W30 (24 QTS)

CHEVRON DELO 400 SAE 10W30 (24 QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		RPL0004775		
	Sample Date		Client Info		23 May 2024		
	Machine Age	mls	Client Info		104890		
	Oil Age	mls	Client Info		22271		
	Filter Age	mls	Client Info		22271		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>100	40		
	Chromium	ppm	ASTM D5185m		<1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	\3	0		
	Aluminum	ppm	ASTM D5185m		7		
	Lead	ppm	ASTM D5185m		, <1		
	Copper	ppm	ASTM D5185m		4		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m	/10	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal		*Visual	NONE	NONE		
<u></u>		scalar	Visuai		INOINE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		10		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	14		
	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.6		
	Nitration	Abs/cm	*ASTM D7624	>20	12.3		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	28.5		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
EL LUD CONDITION							
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3		
The BN result indicates that there is suitable alkalinity remaining in the	Boron	ppm	ASTM D5185m		88		
oil. The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		78		
	Manganese	ppm	ASTM D5185m		1		
	Magnesium	ppm	ASTM D5185m		416		
	Calcium	ppm	ASTM D5185m		1578		
	Phosphorus	ppm	ASTM D5185m		1054		
	Zinc	ppm	ASTM D5185m	1400	1245		
	Sulfur	ppm	ASTM D5185m		3524		
	Oxidation	Abs/.1mm	*ASTM D7414		26.2		
	Base Number (BN)		ASTM D2896		4.9		
	Visc @ 100°C	cSt	ASTM D445	11.1	11.0		







Laboratory Sample No.

Lab Number : 06231247 Unique Number : 11114740 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : RPL0004775 : 09 Jul 2024

Tested : 10 Jul 2024 Diagnosed : 10 Jul 2024 - Don Baldridge RTL PACLEASE - 7009 - Nashville 900 Expo Dr.

Smyrna, TN US 37167 Contact: TECHNICIAN ACCOUNT

Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

catherine.anastasio@wearcheck.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: