

WEAR	
CONTAMINATION	
FLUID CONDITION	NORMAL

- - - -


00	Diesel Engine Fluid {not provided} ( GAL)
The	Machine Id VOLVO L90F 8862 Component


RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		PTK0005520		
Resample at the next service interval to monitor.	Sample Date		Client Info		28 Jun 2024		
	Machine Age	hrs	Client Info		20061		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
				400			
WEAR	Iron	ppm	ASTM D5185m		1		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m	NONE	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	3		
CONTAMINATION	Potassium	ppm	ASTM D5185m		۲ ۲		
There is no indication of any contamination in the oil.	Fuel	ppiii	WC Method		<1.0		
	Water		WC Method		NEG		
	Glycol		WC Method	20.1	NEG		
	Soot %	%	*ASTM D7844	>3	0.1		
	Nitration	Abs/cm	*ASTM D7624		4.5		
	Sulfation	Abs/.1mm	*ASTM D7415		17.8		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.1	NEG		
FLUID CONDITION The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Sodium	ppm	ASTM D5185m		<1		
	Boron	ppm	ASTM D5185m		3		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		57		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		419		
	Calcium	ppm	ASTM D5185m		1970		
	Phosphorus	ppm	ASTM D5185m		1176		
	Zinc	ppm	ASTM D5185m		1439		
	Sulfur	ppm	ASTM D5185m		4419		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	13.4		
	Base Number (BN)	mg KOH/g	ASTM D2896		9.1		
	Vier ( 10000	- 04	AOTA DAAS		40-		

Visc @ 100°C cSt

ASTM D445

14.7





Contact/Location: ALAN PORTERFIELD - LKQBALERD Page 2 of 2