



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 160G 1FF160GXJNF058862
 Component
Diesel Engine
 Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0220207	JR0215412	JR0204120
Sample Date		Client Info		07 Jul 2024	07 May 2024	07 Feb 2024
Machine Age	hrs	Client Info		949	913	500
Oil Age	hrs	Client Info		36	500	500
Filter Age	hrs	Client Info		0	500	500
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>51	5	22	46
Chromium	ppm	ASTM D5185m	>11	0	<1	1
Nickel	ppm	ASTM D5185m	>5	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	2	4	15
Lead	ppm	ASTM D5185m	>26	0	6	8
Copper	ppm	ASTM D5185m	>26	3	24	▲ 215
Tin	ppm	ASTM D5185m	>4	0	1	3
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	5	8	22
Potassium	ppm	ASTM D5185m	>20	<1	<1	7
Fuel		WC Method	>2.1	<1.0	<1.0	0.5
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.4	0.3
Nitration	Abs/cm	*ASTM D7624	>20	6.6	9.7	9.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.0	24.6	25.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	3	4	8
Boron	ppm	ASTM D5185m		242	137	272
Barium	ppm	ASTM D5185m		0	<1	3
Molybdenum	ppm	ASTM D5185m		245	274	423
Manganese	ppm	ASTM D5185m		0	1	6
Magnesium	ppm	ASTM D5185m		807	896	1311
Calcium	ppm	ASTM D5185m		1517	1588	2174
Phosphorus	ppm	ASTM D5185m		935	898	1218
Zinc	ppm	ASTM D5185m		1096	1119	1654
Sulfur	ppm	ASTM D5185m		3482	3421	4187
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.0	19.8	20.1
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	9.8	8.0	7.7
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	13.2	● 11.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0220207 **Received** : 09 Jul 2024
Lab Number : 06231328 **Tested** : 10 Jul 2024
Unique Number : 11114821 **Diagnosed** : 10 Jul 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

CARLTON'S BACKHOE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269
 Contact: LEO

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (704)547-0211

F: