WEAR CONTAMINATION FLUID CONDITION

NORMAL

ABNORMAL


NORMAL

Machine Id

## **BALER 2**

Component Hydraulic System

Fluid (not provided) ( CAL)							
{not provided} ( GAL)							
RECOMMENDATION  We recommend you service the filters on this component. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		PTK0004957		
	Sample Date		Client Info		28 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				ABNORMAL		
WEAR	Iron	ppm	ASTM D5185m	>20	12		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	<1		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>10	2		
	Lead	ppm	ASTM D5185m	>10	2		
	Copper	ppm	ASTM D5185m	>75	18		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	<b>√2</b> 0	5		
There is a moderate amount of visible silt present in the sample.	Potassium	ppm	ASTM D5185m		2		
	Water	PPIII	WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	▲ MODER		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		1		
	Calcium	ppm	ASTM D5185m		77		
	Phosphorus	ppm	ASTM D5185m		316		
	Zinc	ppm	ASTM D5185m		360		
	Sulfur	ppm	ASTM D5185m		2067		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.28		
	Visc @ 40°C	cSt	ASTM D445		42.1		
Report Id: MESBOC [WUSCAR] 06231457 (Generated: 07/11/2024 09:05:09) Rev: 1			Con	tact/Loc	ation: DAVID	SHAFFER	- MESBOC







Certificate L2367

Report Id: MESROC [WUSCAR] 06231457 (Generated: 07/11/2024 09:05:11) Rev: 1

Laboratory Sample No.

: PTK0004957 Lab Number : 06231457 Unique Number : 11114950 Test Package : MOB 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** 

: 11 Jul 2024 Diagnosed : 11 Jul 2024 - Jonathan Hester

16105 FREDERICK RD ROCKVILLE, MD US 20850

**MES RECYCLE** 

Contact: DAVID SHAFFER dshaffer@menv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

: 09 Jul 2024

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: