



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

Mobile Fleet

Machine Id

6452 6452

Component

Diesel Engine

Fluid

MOBIL DELVAC 1300 SUPER 10W30 (8 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0937838	WC0939256	WC0919038
Sample Date		Client Info		08 Jul 2024	23 May 2024	01 Apr 2024
Machine Age	hrs	Client Info		8182	7960	7679
Oil Age	hrs	Client Info		229	559	278
Filter Age	hrs	Client Info		229	559	278
Oil Changed		Client Info		Changed	Changed	Not Changed
Filter Changed		Client Info		Changed	Changed	Not Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	4	5	3
Chromium	ppm	ASTM D5185m	>20	<1	0	0
Nickel	ppm	ASTM D5185m	>4	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	<1	0
Aluminum	ppm	ASTM D5185m	>20	2	4	2
Lead	ppm	ASTM D5185m	>40	<1	0	0
Copper	ppm	ASTM D5185m	>330	8	12	8
Tin	ppm	ASTM D5185m	>15	<1	1	0
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION


There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Silicon	ppm	ASTM D5185m	>25	5	5	3
Potassium	ppm	ASTM D5185m	>20	2	20	1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.2	0.1
Nitration	Abs/cm	*ASTM D7624	>20	5.8	6.2	5.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.7	19.5	18.7
Particles >4µm		ASTM D7647	>20000	5037	6629	4985
Particles >6µm		ASTM D7647	>5000	2744	3611	2716
Particles >14µm		ASTM D7647	>640	467	615	462
Particles >21µm		ASTM D7647	>160	157	207	156
Particles >38µm		ASTM D7647	>40	24	32	24
Particles >71µm		ASTM D7647	>10	2	3	2
Oil Cleanliness		ISO 4406 (c)	>21/19/16	20/19/16	20/19/16	19/19/16
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	12	2
Boron	ppm	ASTM D5185m		51	35	36
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		48	53	54
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		500	693	721
Calcium	ppm	ASTM D5185m		1512	1401	1442
Phosphorus	ppm	ASTM D5185m		704	861	917
Zinc	ppm	ASTM D5185m		875	1048	1107
Sulfur	ppm	ASTM D5185m		2412	3148	3596
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.7	15.7	15.1
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	9.5	9.1	9.7
Visc @ 100°C	cSt	ASTM D445	11.9	10.9	11.3	11.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0937838
Lab Number : 06232162
Unique Number : 11115655
Test Package : CONST (Additional Tests: PrtCount, TBN)

Received : 10 Jul 2024
Tested : 11 Jul 2024
Diagnosed : 11 Jul 2024 - Don Baldrige

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CAROLINA SUNROCK
 PO BOX 25
 BUTNER, NC
 US 27509
 Contact: Leigh Dennis
 rdennis@thesunrockgroup.com
 T: (919)575-4505
 F: (919)575-0162