



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[W68120]
 Machine Id
JOHN DEERE 210G 1FF210GXPNF530543
 Component
Hydraulic System
 Fluid
HITACHI HYDRAULIC SUPER EX 46HN (35 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. (Customer Sample Comment: W68120)

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0220218	JR0188978	JR0170867
Sample Date		Client Info		08 Jul 2024	11 Dec 2023	27 Jun 2023
Machine Age	hrs	Client Info		1471	976	524
Oil Age	hrs	Client Info		1471	976	524
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	Not Changd	Not Changd
Filter Changed		Client Info		N/A	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	16	16	8
Iron	ppm	ASTM D5185m	>32	4	2	1
Chromium	ppm	ASTM D5185m	>9	0	0	0
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>9	<1	0	<1
Lead	ppm	ASTM D5185m	>28	0	0	0
Copper	ppm	ASTM D5185m	>50	1	2	2
Tin	ppm	ASTM D5185m	>5	<1	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>11	1	<1	0
Potassium	ppm	ASTM D5185m	>20	2	0	<1
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	21983	3360	4809
Particles >6µm		ASTM D7647	>20000	4524	1147	1503
Particles >14µm		ASTM D7647	>640	256	253	127
Particles >21µm		ASTM D7647	>160	54	97	32
Particles >38µm		ASTM D7647	>40	1	2	1
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	22/19/15	19/17/15	19/18/14
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	1	<1	<1
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m		<1	0	4
Calcium	ppm	ASTM D5185m		4	13	<1
Phosphorus	ppm	ASTM D5185m	827	540	539	543
Zinc	ppm	ASTM D5185m	0	32	23	31
Sulfur	ppm	ASTM D5185m	13	224	86	141
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.18	0.15	0.14
Visc @ 40°C	cSt	ASTM D445	47	41.8	46.5	46.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0220218 **Received** : 10 Jul 2024
Lab Number : 06232205 **Tested** : 11 Jul 2024
Unique Number : 11115698 **Diagnosed** : 11 Jul 2024 - Don Baldrige
Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CARLTON'S BACKHOE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269
 Contact: LEO

T: (704)547-0211

F: