

## Machine Id

## JOHN DEERE 350P 1FF350PAEPF001239

## **Right Final Drive**

## JOHN DEERE GL-5 80W90 (--- GAL)


RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0222231		
	Sample Date		Client Info		08 Jul 2024		
	Machine Age	hrs	Client Info		486		
	Oil Age	hrs	Client Info		486		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		None		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		118		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		179		
	Chromium	ppm	ASTM D5185m		2		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	15		
There is no indication of any contamination in the component.	Potassium	ppm	ASTM D5185m	>20	<1		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	MODER		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium		ACTM DE10Em	. 51	•		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>01	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		76		
	Barium	ppm	ASTM D5185m		2		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		3		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		23		
	Phosphorus	ppm	ASTM D5185m		492		
	Zinc	ppm	ASTM D5185m		12		
	Sulfur	ppm	ASTM D5185m		15964		


Visc @ 40°C


ASTM D445

cSt

189 --- ---Submitted By: JOHN GUASCHINO







Submitted By: JOHN GUASCHINO Page 2 of 2