WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


[05W47914]

JOHN DEERE 350G 1FF350GXVMF815076

Pump Drive

JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (1 QTS)

JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (1 (13)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0218557	JR0211139	JR0173039
	Sample Date		Client Info		09 Jul 2024	01 Apr 2024	11 May 2023
	Machine Age	hrs	Client Info		3988	3456	2967
	Oil Age	hrs	Client Info		1000	500	2469
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		Changed	Not Changd	N/A
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR	PQ		ASTM D8184		23	20	18
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>151	102	49	58
	Chromium	ppm	ASTM D5185m	>11	1	<1	1
	Nickel	ppm	ASTM D5185m	>10	0	0	0
	Titanium	ppm	ASTM D5185m		<1	0	0
	Silver	ppm	ASTM D5185m		0	0	0
	Aluminum	ppm	ASTM D5185m	>21	6	4	1
	Lead	ppm	ASTM D5185m	>51	0	<1	0
	Copper	ppm	ASTM D5185m	>51	0	0	0
	Tin	ppm	ASTM D5185m	>4	0	<1	<1
	Vanadium	ppm	ASTM D5185m		0	<1	<1
	White Metal	scalar	*Visual	NONE	NONE	NONE	MODER
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>31	26	13	14
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	1	<1	<1
	Water		WC Method	>0.1	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	4	3	2
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		263	316	298
	Barium	ppm	ASTM D5185m		<1	<1	0
	Molybdenum	ppm	ASTM D5185m		238	234	242
	Manganese	ppm	ASTM D5185m		1	<1	1
	Magnesium	ppm	ASTM D5185m		714	762	798
	Calcium	ppm	ASTM D5185m		1454	1459	1427
	Phosphorus	ppm	ASTM D5185m		943	870	925
	Zinc	ppm	ASTM D5185m		964	1037	1073
	Sulfur	ppm	ASTM D5185m		3702	4079	4130
	Visc @ 40°C	cSt	ASTM D445	117	67.4	71.3	69.0







Laboratory Sample No. Lab Number : 06232537

: JR0218557

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received Tested Unique Number : 11116030

Diagnosed

: 11 Jul 2024

: 11 Jul 2024 - Wes Davis

: 10 Jul 2024

US 20136 Contact: DANNY HUFF dhuff@bandssite.com T: (540)270-3203

B & S SITE DEVLEOPMENT

7800 PINEY BRANCH LANE

F: (703)753-0605

Test Package : CONST (Additional Tests: PQ) Certificate L2367

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

BRISTOW, VA