WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

SURVEY - SEAVER [SURVEY-SEAVER]

VOLVO PENTA 3940029356

Port IPS

GEAR OIL SAE 75W90 (4 GAL)

GEAN OIL SAE 13W30 (4 GAL)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
No corrective action is recommended at this time. Resample at the next service interval to monitor.	Sample Number		Client Info		VPA059567		
	Sample Date		Client Info		08 Jul 2024		
	Machine Age	hrs	Client Info		323		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		19		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>275	27		
	Chromium	ppm	ASTM D5185m	>4	<1		
	Nickel	ppm	ASTM D5185m	>4	<1		
	Titanium	ppm	ASTM D5185m	>3	<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>10	2		
	Lead	ppm	ASTM D5185m	>4	<1		
	Copper	ppm	ASTM D5185m	>30	6		
	Tin	ppm	ASTM D5185m	>3	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTANUNATION							
CONTAMINATION The water content is negligible. No other contaminants were detected in the oil.	Silicon	ppm	ASTM D5185m	>35	11		
	Potassium	ppm	ASTM D5185m		5		
	Water	%	ASTM D6304	>0.2	0.166		
	ppm Water	ppm	ASTM D6304	>2000	1660		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	0.2%		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	331		
	Barium	ppm	ASTM D5185m	200	1		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		6		
	Magnesium	ppm	ASTM D5185m	12	92		
	Calcium	ppm	ASTM D5185m		10		
	Phosphorus	ppm	ASTM D5185m		1244		
	Zinc	ppm	ASTM D5185m		10		
	Sulfur	ppm	ASTM D5185m		22639		
	Visc @ 40°C	cSt	ASTM D445		104.2		
					()		







Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : VPA059567 Lab Number : 06232747

Unique Number : 11116240 Test Package: MOB 1 (Additional Tests: KF, PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received **Tested** Diagnosed

: 10 Jul 2024 : 10 Jul 2024

: 10 Jul 2024 - Doug Bogart

US 34677 Contact: MARK WARREN oldsmar@suncoastdmi.com T: (813)475-5942

Suncoast Diesel Marine Inc.

610 Mount Vernan St

OLDSMAR, FL

F: (813)475-5943

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)