



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
SURVEY - SEAVER [SURVEY-SEAVER]

Machine Id
VOLVO PENTA A901951

Component
Starboard Diesel Engine

Fluid
DIESEL ENGINE OIL SAE 15W40 (5 GAL)

RECOMMENDATION

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VPA057288	---	---
Sample Date		Client Info		08 Jul 2024	---	---
Machine Age	hrs	Client Info		330	---	---
Oil Age	hrs	Client Info		0	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		Not Chngd	---	---
Filter Changed		Client Info		Not Chngd	---	---
Sample Status				NORMAL	---	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>80	32	---	---
Chromium	ppm	ASTM D5185m	>6	2	---	---
Nickel	ppm	ASTM D5185m	>2	2	---	---
Titanium	ppm	ASTM D5185m	>2	<1	---	---
Silver	ppm	ASTM D5185m	>2	<1	---	---
Aluminum	ppm	ASTM D5185m	>20	18	---	---
Lead	ppm	ASTM D5185m	>95	5	---	---
Copper	ppm	ASTM D5185m	>85	14	---	---
Tin	ppm	ASTM D5185m	>9	2	---	---
Vanadium	ppm	ASTM D5185m		<1	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	11	---	---
Potassium	ppm	ASTM D5185m	>20	9	---	---
Fuel		WC Method	>4.0	<1.0	---	---
Water		WC Method	>0.1	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	*ASTM D7844		0.3	---	---
Nitration	Abs/cm	*ASTM D7624	>20	8.7	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.1	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.1	NEG	---	---

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>158	3	---	---
Boron	ppm	ASTM D5185m	250	194	---	---
Barium	ppm	ASTM D5185m	10	<1	---	---
Molybdenum	ppm	ASTM D5185m	100	7	---	---
Manganese	ppm	ASTM D5185m		1	---	---
Magnesium	ppm	ASTM D5185m	450	37	---	---
Calcium	ppm	ASTM D5185m	3000	2386	---	---
Phosphorus	ppm	ASTM D5185m	1150	865	---	---
Zinc	ppm	ASTM D5185m	1350	1155	---	---
Sulfur	ppm	ASTM D5185m	4250	3738	---	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.5	---	---
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	8.3	---	---
Visc @ 100°C	cSt	ASTM D445	14.4	14.67	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VPA057288 **Received** : 10 Jul 2024
Lab Number : 06232751 **Tested** : 10 Jul 2024
Unique Number : 11116244 **Diagnosed** : 10 Jul 2024 - Doug Bogart
Test Package : MOB 1 (Additional Tests: TBN)

Suncoast Diesel Marine Inc.
 610 Mount Vernan St
 OLDSMAR, FL
 US 34677
 Contact: MARK WARREN
 oldsmar@suncoastdmi.com
 T: (813)475-5942
 F: (813)475-5943

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)