

Current

History1

History2

Limit/Abn



RECOMMENDATION

Ascendum Machinery Machine Id VOLVO A30G 753663 Component Front Left Final Drive Fluid VOLVO SUPER CEAR OIL 75W 80 CO102 (CAL

VOLVO SUPER GEAR OIL 75W-80-GO102 (--- GAL)

		00				
Resample at the next service interval to monitor.	Sample Number		Client Info		ASC0009683	
	Sample Date		Client Info		05 Jul 2024	
	Machine Age	hrs	Client Info		557	
	Oil Age	hrs	Client Info		557	
	Filter Age	hrs	Client Info		0	
	Oil Changed		Client Info		Not Changd	
	Filter Changed		Client Info		None	
	Sample Status				NORMAL	
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185m		209	
	Chromium	ppm	ASTM D5185m		5	
	Nickel	ppm	ASTM D5185m	>10	1	
	Titanium	ppm	ASTM D5185m		0	
	Silver	ppm	ASTM D5185m		0	
	Aluminum	ppm	ASTM D5185m		<1	
	Lead	ppm		>50	0	
	Copper	ppm	ASTM D5185m		8	
	Tin	ppm	ASTM D5185m	>20	0	
	Vanadium	ppm	ASTM D5185m		0	
	White Metal	scalar	*Visual	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	5	
There is no indication of any contamination in the fluid.	Potassium	ppm	ASTM D5185m	>20	3	
	Water		WC Method	>0.2	NEG	
	Silt	scalar	*Visual	NONE	LIGHT	
	Debris	scalar	*Visual	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	
FLUID CONDITION	Sodium		ASTM D5185m		3	
The condition of the fluid is acceptable for the time in service.	Boron	ppm ppm	ASTM D5185m		289	
	Barium	ppm	ASTM D5185m		0	
	Molybdenum	ppm	ASTM D5185m		9	
	Manganese	ppm	ASTM D5185m		12	
	Magnesium	ppm	ASTM D5185m		<1	
	Calcium	ppm	ASTM D5185m		253	
	Phosphorus	ppm	ASTM D5185m		1332	
	Zinc	ppm	ASTM D5185m		109	
	Sulfur	ppm	ASTM D5185m		23960	
	Guildi	ppm			2000	

Visc @ 40°C

Test

UOM


Method


Submitted By: KARRINGTON RENDLEMAN

100


ASTM D445

cSt









Laboratory

Sample No.

Lab Number : 06233582

Unique Number : 11117075

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

: ASC0009683

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received

Diagnosed

Tested

: 11 Jul 2024

: 12 Jul 2024

Submitted By: KARRINGTON RENDLEMAN Page 2 of 2