WEAR CONTAMINATION FLUID CONDITION

NORMAL

ABNORMAL


NORMAL


Machine Id


15428Component


Component Front Gearbox

GEAR OIL SAE 75W90 (QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
No corrective action is recommended at this time. Resample at the next service interval to monitor.	Sample Number		Client Info		WC0950578		
	Sample Date		Client Info		02 Jul 2024		
	Machine Age	hrs	Client Info		572		
	Oil Age	hrs	Client Info		12103		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				ABNORMAL		
WEAR	Iron	ppm	ASTM D5185m	>200	140		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	1		
	Nickel	ppm	ASTM D5185m	>10	3		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	0		
	Lead	ppm	ASTM D5185m	>50	0		
	Copper	ppm	ASTM D5185m	>200	3		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	<u> </u>		
Elemental level of silicon (Si) above normal indicating ingress of seal material.	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	MODER		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		4		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	161		
	Barium	ppm	ASTM D5185m	200	0		
	Molybdenum	ppm	ASTM D5185m	12	0		
	Manganese	ppm	ASTM D5185m		3		
	Magnesium	ppm	ASTM D5185m	12	0		
	Calcium	ppm	ASTM D5185m		17		
	Phosphorus	ppm	ASTM D5185m		1063		
	Zinc	ppm		125	5		
	Sulfur	ppm	ASTM D5185m		26745		
	Visc @ 40°C	cSt	ASTM D445	109	95.6		











Certificate L2367

Laboratory Sample No.

: WC0950578 Lab Number : 06233622 Unique Number : 11117115 Test Package : CONST

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 11 Jul 2024 **Tested** : 12 Jul 2024

Diagnosed : 13 Jul 2024 - Don Baldridge **SULLIVAN EASTERN INC** 2860 C SLATER RD

MORRISVILLE, NC US 27560

Contact: SCOTT SULLIVAN ssullivan@sullivaneastern.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (919)484-8993 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (919)484-2136