
Cob


WOLVO A30G 752670


Bogie/Center Axle


VOLVO SUPER GEAR OIL 75W-80-GO102 (--- GAL)

VOLVO SUPER GEAR OIL 75W	/-80-GO102	(G	AL)				
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		ASC0008299	VCP0005858	
Trocampio at the next convice interval to memoria.	Sample Date		Client Info		10 Jul 2024	26 May 2023	
	Machine Age	hrs	Client Info		995	514	
	Oil Age	hrs	Client Info		481	514	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	~900	29	124	
	Chromium	ppm	ASTM D5185m		<1	2	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0	0	
	Titanium	ppm	ASTM D5185m	>10	0	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>30	0	5	
	Lead	ppm	ASTM D5185m		0	0	
	Copper	ppm	ASTM D5185m		7	13	
	Tin	ppm	ASTM D5185m		0	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	MODER	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION							
CONTAMINATION	Silicon	ppm	ASTM D5185m		2	3	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		1	6	
	Water		WC Method		NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE NORML	NONE NORML	NONE NORML	
	Appearance Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water		*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		4	2	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		251	191	
	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		2	11	
	Manganese	ppm	ASTM D5185m		2	10	
	Magnesium	ppm	ASTM D5185m		1	6	
	Calcium	ppm	ASTM D5185m		135	848	
	Phosphorus	ppm	ASTM D5185m		2187	1494	
	Zinc	ppm	ASTM D5185m		62	364	
	Sulfur	ppm	ASTM D5185m		28539	25056	
Report Id: ASCCON IWUSCARI 06233639 (Generated: 07/12/2024 14:33:15) Rev: 1	Visc @ 40°C	cSt	ASTM D445		54.2	87.4 By: CLAYT	ON CAUT!!
39000 00 A SELETIN DVIDSEART DRZ 38639 (130021200 DZZZZZZZZZZZZZZZZZZZZZZZZZZZZZZZZZZZ					>unmitte/	1 HV: (:1 A V I	> 1/11 1 F











Certificate L2367

Laboratory Sample No.

: ASC0008299 Lab Number : 06233639 Unique Number : 11117132 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 11 Jul 2024 **Tested** : 12 Jul 2024

Diagnosed : 12 Jul 2024 - Wes Davis

000 - ASCENDUM MACHINERY INC - EXPECT MORE TEAM 1025 INTERNATIONAL DR NW

CONCORD, US 28027

Contact: CELENA SHANK celena.shank@ascendummachinery.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: