

## Machine Id NOT GIVEN HRE0000484 Component Transmission (Auto) Fluid

DEXRON III (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

## **WEAR**

All component wear rates are normal.

## CONTAMINATION

There is no indication of any contamination in the fluid.

## FLUID CONDITION

The condition of the fluid is acceptable for the time in service.

| Test                         | UOM               | Method                     | Limit/Abn | Current     | History1 | History2 |
|------------------------------|-------------------|----------------------------|-----------|-------------|----------|----------|
| Sample Number                |                   | Client Info                |           | HRE0000484  |          |          |
| Sample Date                  |                   | Client Info                |           | 02 Jun 2024 |          |          |
| Machine Age                  | mls               | Client Info                |           | 149144      |          |          |
| Oil Age                      | mls               | Client Info                |           | 0           |          |          |
| Filter Age                   | mls               | Client Info                |           | 0           |          |          |
| Oil Changed                  |                   | Client Info                |           | Changed     |          |          |
| Filter Changed               |                   | Client Info                |           | Changed     |          |          |
| Sample Status                |                   |                            |           | NORMAL      |          |          |
|                              |                   |                            |           |             |          |          |
| Iron                         | ppm               | ASTM D5185m                | >160      | 35          |          |          |
| Chromium                     | ppm               | ASTM D5185m                | >5        | 0           |          |          |
| Nickel                       | ppm               | ASTM D5185m                | >5        | <1          |          |          |
| Titanium                     | ppm               | ASTM D5185m                |           | 0           |          |          |
| Silver                       | ppm               | ASTM D5185m                | >5        | 12          |          |          |
| Aluminum                     | ppm               | ASTM D5185m                | >50       | 32          |          |          |
| Lead                         | ppm               | ASTM D5185m                | >50       | 1           |          |          |
| Copper                       | ppm               | ASTM D5185m                | >225      | 192         |          |          |
| Tin                          | ppm               | ASTM D5185m                | >10       | 13          |          |          |
| Vanadium                     | ppm               | ASTM D5185m                |           | 0           |          |          |
| White Metal                  | scalar            | *Visual                    | NONE      | NONE        |          |          |
| Yellow Metal                 | scalar            | *Visual                    | NONE      | NONE        |          |          |
|                              |                   |                            |           | •           |          |          |
| Silicon                      | ppm               | ASTM D5185m                | >20       | 9           |          |          |
| Potassium                    | ppm               | ASTM D5185m                | >20       | 0           |          |          |
| Water                        |                   | WC Method                  | >0.1      | NEG         |          |          |
| Silt                         | scalar            | *Visual                    | NONE      | NONE        |          |          |
| Debris                       | scalar            | *Visual                    | NONE      | NONE        |          |          |
| Sand/Dirt                    | scalar            | *Visual                    | NONE      | NONE        |          |          |
| Appearance                   | scalar            | *Visual                    | NORML     | NORML       |          |          |
| Odor                         | scalar            | *Visual                    | NORML     | NORML       |          |          |
| Emulsified Water             | scalar            | *Visual                    | >0.1      | NEG         |          |          |
| Sodium                       | ppm               | ASTM D5185m                |           | 7           |          |          |
| Boron                        | ppm               | ASTM D5185m                |           | 91          |          |          |
| Barium                       | ppm               | ASTM D5185m                |           | 0           |          |          |
| Molybdenum                   | ppm               | ASTM D5185m                |           | ۰<br><1     |          |          |
| Manganese                    | ppm               | ASTM D5185m                |           | <1          |          |          |
| Magnesium                    |                   | ASTM D5185m                |           | 2           |          |          |
| Calcium                      | ppm               | ASTM D5185m                |           | 2<br>163    |          |          |
| Calcium                      | ppm               | ASTM D5185m                |           | 289         |          |          |
| Phoenhorue                   |                   |                            |           |             |          |          |
| Phosphorus<br>Zinc           | ppm               |                            |           |             |          |          |
| Phosphorus<br>Zinc<br>Sulfur | ppm<br>ppm<br>ppm | ASTM D5185m<br>ASTM D5185m |           | 48          |          |          |


Visc @ 40°C


cSt

ASTM D445 35.0

Contact/Location: Lisa DePasqua - TOWCHANC

33.9





TOWN OF CHAPEL HILL 6900 MILLHOUSE RD CHAPEL HILL, NC : 13 Jul 2024 - Don Baldridge US 27516 Contact: Lisa DePasqua ldepasqua@townofchapelhill.org T: (919)696-4941 F:



Test Package : FLEET To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received

Diagnosed

Tested

: 11 Jul 2024

: 13 Jul 2024

Laboratory

Sample No.

Lab Number : 06233649

Unique Number : 11117142

: HRE0000484

Contact/Location: Lisa DePasqua - TOWCHANC Page 2 of 2