WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


[W/O 11061]


VOLVO Ecr145 E 317114


Right Travel


VOLVO PREMIUM GEAR OIL 85W-140 GL-5 (1 GAL)

| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|--|------------------|--------|-------------|-----------|-------------|----------|----------|
| The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. | Sample Number | | Client Info | | ML0002063 | | |
| | Sample Date | | Client Info | | 03 Jul 2024 | | |
| | Machine Age | hrs | Client Info | | 491 | | |
| | Oil Age | hrs | Client Info | | 491 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Changed | | |
| | Filter Changed | | Client Info | | N/A | | |
| | Sample Status | | | | NORMAL | | |
| WEAR | Iron | ppm | ASTM D5185m | >500 | 127 | | |
| | Chromium | ppm | ASTM D5185m | | 2 | | |
| Metal levels are typical for a new component breaking in. | Nickel | ppm | ASTM D5185m | | 0 | | |
| | Titanium | ppm | ASTM D5185m | | <1 | | |
| | Silver | ppm | ASTM D5185m | | <1 | | |
| | Aluminum | ppm | ASTM D5185m | >100 | 2 | | |
| | Lead | ppm | ASTM D5185m | >10 | 0 | | |
| | Copper | ppm | ASTM D5185m | >60 | <1 | | |
| | Tin | ppm | ASTM D5185m | >5 | 12 | | |
| | Vanadium | ppm | ASTM D5185m | | <1 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | ×150 | 13 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185m | | 2 | | |
| | Water | ррпп | WC Method | | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| FLUID CONDITION | Sodium | nnm | ASTM D5185m | | <1 | | |
| | Boron | ppm | ASTM D5185m | 111 | <1 | | |
| The condition of the oil is acceptable for the time in service. | Barium | ppm | ASTM D5185m | | 2 | | |
| | Molybdenum | ppm | ASTM D5185m | | <1 | | |
| | Manganese | ppm | ASTM D5185m | | 3 | | |
| | Magnesium | ppm | ASTM D5185m | | 1 | | |
| | Calcium | ppm | ASTM D5185m | | 4 | | |
| | Phosphorus | ppm | ASTM D5185m | | 305 | | |
| | Zinc | ppm | ASTM D5185m | | 16 | | |
| | Sulfur | ppm | ASTM D5185m | | 16175 | | |
| | Visc @ 40°C | cSt | ASTM D445 | | 137 | | |











Certificate L2367

Laboratory Sample No.

Lab Number : 06234092 Unique Number : 11122926 Test Package : CONST

: ML0002063

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 11 Jul 2024

Tested : 12 Jul 2024 Diagnosed : 14 Jul 2024 - Don Baldridge **RELIABLE CONTRACTING**

2410 EVERGREEN RD SUITE 200 $\mathsf{GAMBRILLS}, \mathsf{MD}$

US 21054

T: (410)987-1851

Contact: RUSSELL HATFIELD RHATFIELD@RELIABLECONTRACTING.COM

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: