



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
944012
 Component
Natural Gas Engine
 Fluid
PETRO CANADA DURON GEO LD 15W40 (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0119102	GFL0115483	GFL0106964
Sample Date		Client Info		10 Jul 2024	22 Mar 2024	16 Dec 2023
Machine Age	hrs	Client Info		21520	15735	15170
Oil Age	hrs	Client Info		15170	565	550
Filter Age	hrs	Client Info		15170	565	550
Oil Changed		Client Info		Changed	Not Changd	Changed
Filter Changed		Client Info		Changed	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	16	20	20
Chromium	ppm	ASTM D5185m	>4	<1	0	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	5	2	<1
Lead	ppm	ASTM D5185m	>30	<1	1	1
Copper	ppm	ASTM D5185m	>35	2	<1	<1
Tin	ppm	ASTM D5185m	>4	0	<1	0
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>+100	3	3	3
Potassium	ppm	ASTM D5185m	>20	21	10	6
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.8	1.5	1.5
Nitration	Abs/cm	*ASTM D7624	>20	11.7	10.4	10.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.3	20.6	21.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		27	17	17
Boron	ppm	ASTM D5185m	50	4	4	1
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	50	58	59	56
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	560	716	882	816
Calcium	ppm	ASTM D5185m	1510	1418	1070	998
Phosphorus	ppm	ASTM D5185m	780	875	1039	898
Zinc	ppm	ASTM D5185m	870	1140	1251	1102
Sulfur	ppm	ASTM D5185m	2040	2555	3418	2742
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.9	16.7	16.7
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	6.4	8.7	8.7
Visc @ 100°C	cSt	ASTM D445	15.1	13.9	12.6	12.8


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0119102 **Received** : 12 Jul 2024
Lab Number : 06234546 **Tested** : 12 Jul 2024
Unique Number : 11123380 **Diagnosed** : 12 Jul 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 882 - Gainesville
 5002 SW 41st Blvd
 Gainesville, FL
 US 32608
 Contact: ROBERT CLARK
 robert.clark@gflenv.com
 T:
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)