



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
944008
 Component
Natural Gas Engine
 Fluid
PETRO CANADA DURON GEO LD 15W40 (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0119103	GFL0115482	GFL0106961
Sample Date		Client Info		10 Jul 2024	22 Mar 2024	16 Dec 2023
Machine Age	hrs	Client Info		13542	12955	12275
Oil Age	hrs	Client Info		587	680	187
Filter Age	hrs	Client Info		587	680	187
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	16	21	3
Chromium	ppm	ASTM D5185m	>4	<1	0	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	4	2	1
Lead	ppm	ASTM D5185m	>30	<1	<1	1
Copper	ppm	ASTM D5185m	>35	2	<1	<1
Tin	ppm	ASTM D5185m	>4	0	<1	0
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>+100	3	3	3
Potassium	ppm	ASTM D5185m	>20	19	10	0
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.8	1.5	0.1
Nitration	Abs/cm	*ASTM D7624	>20	11.8	10.4	8.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.1	20.6	18.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		26	17	4
Boron	ppm	ASTM D5185m	50	4	4	26
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	50	57	60	48
Manganese	ppm	ASTM D5185m	0	0	<1	0
Magnesium	ppm	ASTM D5185m	560	708	894	528
Calcium	ppm	ASTM D5185m	1510	1367	1070	1414
Phosphorus	ppm	ASTM D5185m	780	841	1065	704
Zinc	ppm	ASTM D5185m	870	1102	1261	871
Sulfur	ppm	ASTM D5185m	2040	2405	3462	2288
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.9	16.6	16.1
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	6.4	8.7	7.6
Visc @ 100°C	cSt	ASTM D445	15.1	13.8	12.7	14.6


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : GFL0119103
 Lab Number : 06234547
 Unique Number : 11123381
 Test Package : FLEET

Received : 12 Jul 2024
 Tested : 12 Jul 2024
 Diagnosed : 12 Jul 2024 - Wes Davis

GFL Environmental - 882 - Gainesville
 5002 SW 41st Blvd
 Gainesville, FL
 US 32608
 Contact: ROBERT CLARK
 robert.clark@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: